THE STATISTICAL MECHANICS OF CONTINUOUS RANDOM NETWORKS

Konstantin A. Shakhnovich, Ph.D.
Department of Physics
University of Illinois at Urbana-Champaign, 2001
Paul M. Goldbart, Advisor

Under sufficient permanent random covalent bonding, a fluid of atoms or small molecules is transformed into an amorphous solid network. Being amorphous, local structural properties in such networks vary across the sample. A natural order parameter, resulting from a statistical-mechanical approach, captures information concerning this heterogeneity via a certain joint probability distribution. This joint probability distribution describes the variations in the positional and orientational localization of the particles, reflecting the random environments experienced by them, as well as further information characterizing the thermal motion of particles. A complete solution, valid in the vicinity of the amorphous solidification transition, is constructed essentially analytically for the amorphous solid order parameter. Knowledge of this order parameter allows us to draw certain conclusions about the stucture and heterogeneity of randomly covalently bonded atomic or molecular network solids in the vicinity of the amorphous solidification transition. These conclusions are then compared to the results of molecular-dynamics simulations of the model and are found to be in good agreement with them. Results of simulations of the system far from the transition are also presented. Robustness of the results of the simulations supports the conclusion that the results obtained are not limited to the context of the particular model presented here, but are, instead, a consequence of the symmetries of the system.

THE STATISTICAL MECHANICS OF CONTINUOUS RANDOM NETWORKS

BY

KONSTANTIN A. SHAKHNOVICH

B.A., University of Chicago, 1996

THESIS

Submitted in partial fulfillment of the requirements
for the degree of Doctor of Philosophy in Physics
in the Graduate College of the
University of Illinois at Urbana-Champaign, 2001

Urbana, Illinois

ABSTRACT

Under sufficient permanent random covalent bonding, a fluid of atoms or small molecules is transformed into an amorphous solid network. Being amorphous, local structural properties in such networks vary across the sample. A natural order parameter, resulting from a statistical-mechanical approach, captures information concerning this heterogeneity via a certain joint probability distribution. This joint probability distribution describes the variations in the positional and orientational localization of the particles, reflecting the random environments experienced by them, as well as further information characterizing the thermal motion of particles. A complete solution, valid in the vicinity of the amorphous solidification transition, is constructed essentially analytically for the amorphous solid order parameter. Knowledge of this order parameter allows us to draw certain conclusions about the stucture and heterogeneity of randomly covalently bonded atomic or molecular network solids in the vicinity of the amorphous solidification transition. These conclusions are then compared to the results of molecular-dynamics simulations of the model and are found to be in good agreement with them. Results of simulations of the system far from the transition are also presented. Robustness of the results of the simulations supports the conclusion that the results obtained are not limited to the context of the particular model presented here, but are, instead, a consequence of the symmetries of the system.

To my parents

ACKNOWLEDGMENTS

I would like to thank my advisor for his invaluable guidance.

This work was supported by the National Science Foundation through grants NSF DMR99-75187, NSF DMR94-24511, NSF DMR91-57028, and through the Graduate Research Training fellowship NSF GER93-54978, by the Materials Computation Center via grant NSF DMR99-78550, and by the Campus Research Board of the University of Illinois at Urbana-Champaign.

TABLE OF CONTENTS

LIST OF FIGURES

CHAPTER 1

INTRODUCTION AND OVERVIEW

It is quite remarkable that despite the many recent advances in physics and materials science a whole class of materials still present a significant mystery to science, having defied both adequate theoretical description and study by means of numerical simulations. This class of materials, termed *glassy systems*, is ubiquitous, its most common member something as ordinary as window glass. Despite the fact that glass has been known to humanity since antiquity, many fundamental questions remain unanswered.

The two quintessential features of glassy systems that make attempts at their theoretical descriptions challenging are these: (i) glassy systems are *amorphous*, and (ii) there is no clear *separation of timescales*. Let us elaborate on these two points.

First, as we mentioned, glassy systems are amorphous. What we mean by this in the present context is that, unlike crystals, they do not exhibit long-range order. This is best represented by the fact that X-ray scattering, as we shall discuss in more detail in Sec. 2.2, does not detect any periodicity in the atomic positions. [1] On an intuitive level, this means that in the case of a crystal, as in Fig. 1.1 (a), given the positions of a few atoms (e.g., the four black ones) we would be able to reconstruct the entire sample fairly accurately (meaning that we would be able do determine the equilibrium positions of all the atoms), whereas in the case of an amorphous system, as in Fig. 1.1 (b), we would at best be able to fairly accurately reconstruct only the locations of a few nearby



Figure 1.1 Snapshots of a crystalline solid, a liquid/amorphous solid, and a gas – see text for details

atoms. It is important to note, however, that lack of long-range order does not imply lack of order entirely – on short lengthscales the order is indeed very strong. This is best illustrated by the fact that if, in Fig. 1.1 (b), the atom with the dotted outline (or any other atom) were removed, it would be easy to reconstruct its position fairly accurately from the positions of the neighboring atoms. In contrast, in Fig. 1.1 (c), which represents a snapshot of a system without even short-range order (i.e., a gas), reconstructing the position of the atom with the dotted outline would be essentially impossible. Thus, in a snapshot, an amorphous solid would look very similar to a liquid (but very different from a crystal or a gas) – both exhibit short-range, but not long-range, order.

The second property of glassy systems that we would like to examine in more detail is the lack of a clear *separation of timescales*. As discussed in Ref. [2], presumably, the glassy state arises when certain correlations in the system become long-lived, i.e., become unable to relax on the timescales associated with the relaxation of the thermal degrees of freedom. If these correlations were infinitely long-lived (that is, so long-lived as to be considered permanent on the timescale of possible experiments), then a theoretical model would be able to exploit this *separation of timescales* by applying the full power of the methods of *equilibrium* statistical mechanics to the thermal degrees of freedom, treating the constraints on the motions of the atoms as *extrinsic* (i.e., externally imposed, rather than *intrinsic*, i.e., internally generated). Unfortunately, it appears that in many glassy systems these correlations are often not sufficiently long-lived to allow for such an approximation. Presumably, as the atoms rearrange themselves by undergoing thermal motion subject to maintaining certain correlations, so too the correlations form and dissipate under the influence of the changing atomic positions. This creates a "feedback loop,' which renders the system not amenable to equilibrium statistical mechanics, as any treatment would have to face the full (and no doubt exceedingly complicated) inherent dynamics of the system.

Having elaborated on these two defining features of glassy systems, let us turn to an example of how complicated seemingly simple questions can become in the presence of these features. Consider this question, which has been the subject of much controversy: should glass be considered a solid or an (extremely viscous) liquid? While it is not our intention to attempt to resolve this dilemma here, examining the reasons behind its subtlety brings to the foreground the essential features of glassy systems. First and foremost, we must define what it really means for a material to be a solid as opposed to a liquid. From a theoretical point of view, solids are distinguished by the existence of correlations in the system that are both long-lived (that is, persist on timescales much longer than those associated with the relaxation of the thermal degrees of freedom) and long-ranged (that is, persist over lengthscales much larger than the inter-atomic separation). In systems where a separation of timescales is present, it is reasonable to treat these long-lived correlations as having *infinite* lifetimes and, consequently, model the system as a solid. However, if separation of timescales is absent, the question of whether a system should, from a theoretical point of view, be treated as a solid becomes quite complicated.

Presence of these long-lived correlations, which distinguish the solid state, has important implications, both microscopic and macroscopic. Let us examine some of the practical implications. Macroscopically, long-range correlations in atomic positions give rise to a a non-zero shear modulus: in response to an infinitesimal zero-frequency shear stress the solid develops an infinitesimal zero-frequency shear strain; liquids, in contrast, do not. In everyday terms this fact is expressed through the notion that liquids "flow" whereas solids do not. It must be noted that infinitesimal zero-frequency shear stress is a theorist's abstraction – any real experiment will have both a finite timescale and a finite lengthscale associated with it. An experimental determination of the timescale on which glass might "flow" can thus be very difficult, as that timescale can be very long, a fact that is best illustrated by the use of glass in vertical window panes. The situation is further complicated by the fact that even materials that are *bona fide* solids, such as crystalline metals (e.g., lead) do, due to defect motion, in a certain sense flow, albeit, again, very slowly. Thus, a conclusive experiment that would, by means of macroscopic stress measurements, determine whether glass is a liquid or a solid is challenging. This is a consequence of both the lack of *separation of timescales* and the amorphous nature of glass: in the case of lead, defect motion takes place on much longer timescales than the relaxation of the thermal degrees of freedom, whereas in the case of glassy systems the thermal motion and the structural rearrangements may coexist on comparable timescales; in addition, due to lack of long-range order we cannot easily detect the propagation of faults through the system (in fact, the whole notion of faults is inapplicable to glassy systems).

Microscopically, long-lived correlations in atomic positions manifest themselves in the fact that the particles (atoms or small molecules) that solids consist of are usually localized in space. This means that, though undergoing thermal motion on short timescales, on much longer timescales they still remain in the vicinity of their mean or equilibrium positions.[1] In contrast, the constituent elements of a liquid will, given enough time, wander through the whole sample, as illustrated in Fig. 1.2. It is important to note that on



Figure 1.2 The difference in thermal motion for atoms in the solid and liquid states

short timescales constituent particles in either a liquid or a solid undergo nearly identical thermal motion. Again, the lack of a separation of timescales, together with the lack of long-range order, precludes the staging of a conclusive experiment to determine if glass is a liquid or a solid: when looking at a snapshot of an amorphous solid, an observer would not be able to determine the (mechanical) equilibrium positions of the atoms. As it is impossible to track individual atoms, it becomes impossible to determine whether on long timescales the atoms in a glass remain localized or, instead, explore the whole sample.

Thus we see how the combination of a lack of a *separation of timescales* together with a lack of long-range order presents challenges to both the theorist and the experimenter. To make progress, we believe it is worthwhile to study simpler model systems, i.e., systems that are amorphous but in which, in contrast to conventional glassy systems, a clear and evident separation of timescales is present. We would like to, in effect, cut the "feedback loop": the particles will undergo thermal motion subject to certain constraints, but

[1] Strictly speaking, owing to, e.g., vacancy diffusion, this identification of solidity and localization of individual particles is not valid for, say, elemental solids. However, the systems that we shall focus on shall be covalently bonded solids, for which vacancy diffusion is not a noticeable effect, so in the case of the phase transitions that we shall study, as we shall see later, localization of individual particles and solidification will coincide.

the constraints themselves shall be imposed externally and be very long-lived, so that equilibrium statistical mechanics can legitimately be applied to the thermal degrees of freedom. Such an approach would allow us to study the effects of random constraints on the system and the properties of the amorphous state that they give rise to. It must be noted, of course, that no constraint can truly be permanent – every chemical bond has a finite energy scale and, hence, a finite lifetime; but in many cases this lifetime is sufficiently long that the assumption of a *separation of timescales* is valid. In such a system, the constraints imposed on the motion of the atoms would artificially *quench in* certain correlations, thereby allowing us to study the phase transition from a liquid to an amorphous solid as the number of constraints is increased. By studying this transition we can gain insight into the nature of these amorphous systems (characterized by the separation of timescales), which, in turn, will lead to a better understanding of the nature of conventional glassy systems (characterized by the importance of the "feedback loop").

As it turns out, there exists a substantial class of materials having just the required properties. The classic examples include vulcanized rubber, in which very long-lived sulfur bonds bind long polymer molecules together, and silica (and other) gels, in which individual molecules can (by means of a reduction reaction) form covalent bonds with one another.

In this work, we will concentrate on the latter example, it being closer in structure to conventional glassy systems (window glass, in particular). We will address the statistical structure of the amorphous solid state via a simple model of a three-dimensional vitreous medium consisting of covalently bonded atoms (or low-molecular-weight molecules). We shall do so essentially analytically, by making use of techniques drawn from the field of the statistical mechanics of systems having quenched randomness [3]. Results of molecular dynamic simulations of this model will also be reported.

The model of vitreous media on which we shall focus is that introduced by Goldbart and Zippelius [4], which takes as ingredients a thermodynamically large number of particles between which some large number of permanent random covalent bonds are introduced. The quenched randomness is encoded in the information describing which pairs of particles are covalently bonded; the remaining (annealed) degrees of freedom correspond to the unconstrained positions of the particles and the orientations of the orbitals. This model exhibits a continuous equilibrium phase transition from the liquid state to the amorphous solid state when the density of introduced bonds exceeds a certain critical value. It is on the structure and heterogeneity of this state that we hope to shed some light.



Figure 1.3 Structure of silica gel (in two dimensions).

As an example of the type of medium we have in mind, consider networks formed by the polycondensation of $Si(OH)_4$ molecules, during which H_2O is eliminated between pairs of hydroxyl (OH) groups on certain randomly selected pairs of $Si(OH)_4$ molecules so as to form Si–O–Si bonds (Fig. 1.3 illustrates the structure of silica gel). The amorphous solidification of such media has been studied in many experiments; we cite as an example those of Gauthier-Manuel et al. [5].

As it is our intention to develop a rather general model of random networks, and to focus on universal properties, it is not necessary to incorporate the specific details of the medium. For example, we shall not be accounting for the bond geometry associated with the so-called bridging oxygen atoms between the silicon atoms. In the model, both types of Si orbitals, those connected to hydroxyl groups and those connected to bridging oxygen atoms, will simply be referred to as "orbitals." A second example of the type of media we have in mind is provided by amorphous silicon networks [1], especially those in which hydrogen passivates bonds unconnected to other silicon atoms.

The structural characterization of the vitreous state that we shall construct will be statistical in nature, reflecting the intrinsic heterogeneity of the environments that the constituent particles in vitreous media inhabit. It will take the form of a *joint probability distribution* characterizing the fraction of particles that are localized in the vitreous state, and will describe the spatial extent of the thermal fluctuations in their positions, the degree and character of the thermal fluctuations in the orientations of the orbitals that are capable of participating in covalent bonds, and the strength and nature of the correlations between the thermal fluctuations in the particle positions and the orbital orientations. Moreover, rather than dealing with media having a specific architecture (i.e., a specific realization of introduced bonds), we shall consider an ensemble of architectures, all characterized by a common parameter governing the probability that a permanent chemical bond was formed between any pair of nearby orbitals.

A statistical description of an amorphous solid state has previously been developed and explored in the context of vulcanized (i.e., randomly permanently crosslinked) *macromolecular* media [6, 7]. This description, which addresses the distribution of spatial extents of thermal position-fluctuations (i.e., localization lengths) has been confirmed by computer simulations [8], and rather general, model-nonspecific arguments in favor of the broad applicability of the description have also been presented [9]. For any particular version of random media (e.g. the macromolecular media of Refs [6, 7] or the vitreous media considered in the present work), what determines the specific content of the statistical description of the amorphous solid state is the form of the random constraints that the permanent covalent bonding imposes, and the resultant form taken by the amorphous solid order parameter. In the present context of vitreous media, the constraints, as we shall see below, are more intricate than they are in the macromolecular vulcanization context and, accordingly, the order parameter is more intricate and the statistical content more elaborate: it accounts not only for the heterogeneity (i.e., the distribution over the sample) of positional localization lengths but also for the distribution of orbital-orientation thermal fluctuations, the strengths of the position-angle thermal fluctuation correlations, and the statistical correlations between these physical characteristics.[2]

In Ref. [4], in addition to introducing the model of random network forming media considered here, and formulating the question of the phase transition to (and structure of) the amorphous solid state via statistical-mechanical techniques, Goldbart and Zippelius made a simple variational mean-field theory for the amorphous solid state in which all particles shared a common localization length and all orbitals shared a common extent of their angular localization. The positional and angular localization parameters were then solved for, self-consistently, and it was found that, at a certain critical value of the density of formed bonds, a continuous transition to an amorphous solid state occurs, beyond which the inverse of the positional localization parameter grows continuously from zero. It was also found that, in response to the onset of positional localization, orientational localization of the orbitals sets in. Owing to the restricted form of the variational hypothesis for the order parameter adopted in Ref. [4], specifically that it did not allow for the possibility that only a fraction of the particles would become localized at the transition, the critical bond density was over-estimated in Ref. [4]. (The correct critical density was, however, known from the linear stability analysis of the fluid state.) Later

[2]What we, in fact, compute are moments of averages of such distributions over realizations of the quenched randomness. Although we have not checked this point in detail, we do not expect there to be sample-to-sample variations of the distribution.

work by Theissen et al. [10], in addition to allowing for networks comprising particles of various valencies, cured the difficulty of the critical bond density, by broadening the variational hypothesis to allow for a localized fraction (although it still only allowed for a single value for the positional and orientation localization parameters, and did not account for correlations between the thermal fluctuations of positions and orientations).



Figure 1.4 Structure of the amorphous solid state. Note the large disordered molecule and the clusters of molecules disconnected from it.

What, then, is the nature of the amorphous solid state? If the number of permanent random covalent bonds introduced between particles is smaller than a certain critical value then the effect of these bonds is to bind at least some of the particles into random permanent molecules of a variety of types (varying in size and architecture), each of which, given sufficient time, will wander ergodically through the volume of the container, i.e., the equilibrium state of the system is fluid. If, however, the number of bonds introduced is greater than the critical value then their effect is to bind a nonzero fraction of the particles into a *macroscopically large disordered molecule* that extends throughout the container, the remaining fraction of particles remaining disconnected from the macroscopic molecule and capable of wandering across the container, given sufficient time (see Fig. 1.4 for an illustration). By contrast, the particles that constitute the extensive molecule will be localized in the vicinity of random preferred spatial positions, about which their positions will undergo thermal fluctuations extending only over a limited spatial regime (which will vary randomly in magnitude from particle to particle, reflecting the random architecture of the network), and these particles will confer a rigidity on the entire system, so that the equilibrium state of the system will no longer be fluid and will, instead, be solid. [3] Moreover, the orbitals attached to localized particles will exhibit most probable orientations, about which they will fluctuate thermally, the extent and nature of these fluctuations also varying randomly from orbital to orbital. In addition, the thermal fluctuations in the positions of the particles and the orientations of the bonds connecting them will be correlated, to an extent that varies randomly from particle to particle. The unconventional nature of this the amorphous solid state is worth emphasizing: (i) only a fraction of the particles will be localized; (ii) the mean positions of the localized particles will be random, as will be (iii) the spatial extent of the positional fluctuations of the particles, (iv) the orientational fluctuations of the orbitals, and (v) the correlations between these fluctuations (these parameters being characterized by a joint probability distribution); and (vi) there will be no hint of crystallinity beyond the shortest of lengthscales (i.e., the bond length), beyond these lengthscales the symmetries of the amorphous solid state being those of the liquid state.

Our principal aims are to construct a statistical characterization of the structure and heterogeneity of the amorphous solid state exhibited by a model of permanently randomly bonded vitreous media in the vicinity of the solidification transition, to provide a physical interpretation of this characterization, and to further explore the system by means of computer simulations, both to test the predictions of the theory and to explore

[3] As was mentioned above, macroscopically solids are characterized by their having a nonzero shear modulus. As only a small fraction of particles constitute the extensive molecule, the kind of experiment that we envision to measure the shear modulus would be using a pair of plates with prongs to shear the system. In such an experiment we can be sure that the prongs will "catch" the extensive molecule, so that we would, in fact, be measuring the shear modulus of the system. By contrast, an experiment involving a pair of plates without prongs might probe the viscosity of the remaining fluid, consisting of the remaining smaller molecules.

the system in regimes in which some of our theoretical assumptions are invalid. We shall develop the theoretical framework by constructing the self-consistency equation for the amorphous solid order parameter, valid in the vicinity of the solidification transition, and obtaining an exact solution of this self-consistent equation. We will then explore the results of molecular dynamical simulations and compare these results with theoretical predictions.

This Thesis is organized as follows. In Chapter 2 we shall proceed kinematically, describing the model that we shall be considering, and analyzing a suitable order parameter defined in terms of the positions of the constituent particles and the orientations of their orbitals. Continuing kinematically, we shall explore the structure of this order parameter, and elucidate the physical information that it encodes. Then, in Chapter 3, we shall address the model, regarding the formed bonds as quenched random variables that vary from realization to realization. By using equilibrium statistical mechanics, invoking the replica technique to deal with the quenched randomness, and making a mean-field hypothesis, we shall develop a self-consistent equation for the order parameter. By making a natural physical hypothesis for the form of the solution we shall, in Chapter 4, solve exactly for this order parameter in the regime in which the thermal fluctuations of the particle positions and orbital orientations are strong (i.e., near the solidification transition). In Chapter 5 we shall extract from our solution a wide array of physical diagnostics characterizing the amorphous solid state. Chapter 6 will be devoted to the description and presentation of the results of a molecular-dynamics simulation of a system based on the theoretical model, aimed at verifying the theoretical predictions as well as exploring the system outside the domain of validity of the theoretical assumptions. It is worth emphasizing that with the exception of Chapter 6, throughout this work we shall be proceeding analytically, except that we shall make use of the numerically-obtained scaling function (of a single variable) central to the characterization of vulcanized macromolecular matter described in Refs. [6, 7]. Lastly, Chapter 7 will contain some concluding remarks and perspective for future research directions.

CHAPTER 2

MODEL AND ORDER PARAMETER

2.1 Elements of the Model

The model of vitreous media which we shall focus on is that introduced in Ref. [4], which takes as its ingredients a thermodynamically large number N of particles, moving in a large three-dimensional cube of volume V (on which we impose periodic boundary conditions), at least some of which particles are permanently randomly bonded together to form a random network. At the kinematic level, the particles (labeled by $j = 1, \ldots, N$) are characterized by their position vectors $\{\mathbf{c}_j\}_{j=1}^{N}$, along with the NA unit vectors $\{\mathbf{s}_{j,a}\}_{a=1}^{A}{}_{j=1}^{N}$ describing the spatial orientations of the A orbitals that radiate from each of the particles j. These orbitals represent the particle's ability to form covalent chemical bonds with other such particles. Note that we shall be measuring lengths in units such that orbitals have length unity. Figure 2.1 illustrates the structure of the particles and the formation of a continuous random network out of them.

The orbitals radiating from a given particle tend to repel one another. For example, in the absence of any external perturbing forces, all things being equal, the orbitals of a four-orbital particle would point towards the vertices of a regular tetrahedron, as shown in Fig. 2.1(a). Rather than give a detailed specification of the interactions that embody this orbital-orbital repulsion, we shall encode the effects of such interactions into a sequence



Figure 2.1 Particle structure, bond, and network formation. (a) A single particle with the near-tetrahedral equilibrium configuration of its orbitals. In this example the number of orbitals per atom A is 4 (as would be the case, e.g., for networks of Si atoms). (b) Formation of a covalent bond between two particles (the participating orbitals are slightly separated, for clarity). (c) A collection of three particles bonded together, forming the beginnings of a random network.

of parameters that characterize the correlations between the orientations of the orbitals of a single particle. For example, we shall find ourselves needing the correlator of the orientations of two *distinct* orbitals (a_1 and a_2) of a single particle (in the fluid state), say the j^{th}:

$$\left\langle Y^*_{\ell_1 m_1}(\mathbf{s}_{j,a_1})\, Y_{\ell_2 m_2}(\mathbf{s}_{j,a_2})\right\rangle_{1,1} = \frac{1}{4\pi}\,\delta_{\ell_1,\ell_2}\,\delta_{m_1,m_2}\,C_\ell, \tag{2.1}$$

where the $Y_{\ell m}$ are spherical harmonics. We have parameterized this correlator in terms of the real numbers $\{C_\ell\}_{\ell=0}^{\infty}$ (with $C_0 \equiv 1$) that reflect the extent to which the orbitals interact.[1] The angle brackets $\langle \cdots \rangle_{1,1}$, which we discuss below in Sec. 3.1.1, denote thermal averaging with respect to a the single-particle Hamiltonian, which incorporates the inter-orbital interactions.[2] The form of this correlator follows from the isotropy of the

[1]From the addition theorem for spherical harmonics, tracing Eq. (2.1) over m we find $C_\ell = \left\langle P_\ell(\mathbf{s}\cdot\mathbf{s}')\right\rangle$. We also note, in passing, that the special case of uncorrelated (free) orbitals corresponds to the set of parameters $C_\ell = (1, 0, \ldots, 0)$.

[2]Since the angle brackets denote thermal averages, strictly speaking the C_ℓ parameters measure the strength of the inter-orbital repulsion as compared to the thermal energy scale kT

distribution of the orbital orientations in the fluid state. We shall not find ourselves making explicit use of the correlator of the orientations of *three* distinct orbitals of a single particle. However, a simple symmetry-dictated form for it can readily be constructed, by making use of Wigner 3-j technology, if one wishes to compute explicitly components of the order parameter that depend on it.

Having described the issue of a single particle and its orbitals, we now turn to the issue of the permanent random covalent bonds between pairs of particles, and how we are to describe them. We regard such bonding as introducing constraints on the relative location and relative orientation of the particles and orbitals participating in the bond. Specifically, we model the situation in which particles j and j' are bonded via orbitals a and a' by the constraints

$$\mathbf{c}_j + \frac{1}{2}\mathbf{s}_{j,a} = \mathbf{c}_{j'} + \frac{1}{2}\mathbf{s}_{j',a'}, \tag{2.2}$$

$$\mathbf{s}_{j,a} = -\mathbf{s}_{j',a'}, \tag{2.3}$$

as shown in Fig. 2.1(b). We denote by the number M and the collection $\{j_e, j'_e; a_e, a'_e\}_{e=1}^{M}$ a specific realization of M bonds (i.e. a specific chemical architecture).

Of course, the particles in the fluid interact with one another, regardless of whether or not bonds have been introduced. We shall assume that pairwise interactions, depending on the relative separation and orientation of the orbitals, exist between all particles. The crucial consequence that we assume these interactions to have is that they stabilize the system with respect to the formation of macroscopically inhomogeneous or anisotropic states, such as regular crystalline, liquid crystalline, molecular crystalline or, if a solvent is present, phase-separated states.

2.2 Amorphous Solid Order Parameter: Random Positional and Orientational Localization

Having proposed a semi-microscopic model of vitreous media we must now construct a mathematical object that is capable of detecting the amorphous solid state, i.e., a suitable order parameter. Such an order parameter would have not only to detect the localization of individual elements of the system (in the case of vitreous media: atoms and bonds), but also to distinguish between crystalline and amorphous solid states. In developing such an order parameter, we will be following the ideas of Ref. [4], which represent an elaboration of ideas discussed in Refs. [11, 12, 13].

Let us first consider an individual particle. Pick a wavevector $\mathbf{k}$ and consider the entity $\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j)\rangle$, where $\mathbf{c}_j$ is the position vector of particle j and angle brackets denote thermal (or long-time) averaging. If the particle is delocalized (i.e., allowed to explore the whole system over time) then this object has the value zero. If, however, the particle is part of the infinite random network, then it is localized on some lengthscale ξ, and thus the object $\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j)\rangle$ will be of order unity for wavevectors of magnitude k less than, or of order of, ξ^{-1}. Thus, this object is capable of detecting the positional localization of a single particle. Similarly, if a particle's orbital is not orientationally localized (i.e., has an equal probability of pointing in any direction), then the object $\langle Y_{\ell m}(s_{j,a})\rangle$ will have value zero for all values of ℓ and m. If, however, the particle is part of the infinite network, then its orbital will be localized (i.e., have a preferred orientation in space), and $\langle Y_{\ell m}(s_{j,a})\rangle$ will be nonzero at least for some values of ℓ and m. Thus this object can serve to detect the angular localization of a single bond. The object $\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j)Y_{\ell m}(s_{j,a})\rangle$ would then serve to detect both the localization of an atom and a bond attached to it simultaneously. It is important to note that in addition to being able to simultaneously detect the positional localization of a single particle and the orientational localization of a single orbital the object $\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle$ encodes information about the correlations in the thermal fluctuations in the position of a particle and the orientation of its orbitals as well.

Perhaps, then, an average of such factors over all the atoms and bonds in the sample, i.e., the object

$$\frac{1}{NA \sum_{j=1}^{N} \sum_{a=1}^{A} \langle \exp(i\mathbf{k}\cdot\mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle} \tag{2.4}$$

would be capable of detecting the amorphous solid state? This naive expectation turns out to be untrue. Indeed, the positions of the atoms in the system, as well as the orientations of the orbitals, are random, both in the solid and in the liquid states. Thus the factors $\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle$, although many of them are nonzero (for suitable $\mathbf{k}$, ℓ, m), would, for a large enough sample, add destructively to give 0. It is worth noting that in the case of a hypothetical crystal made up of particles constrained to be localized near the vertices of a regular lattice (rather than at random positions in space) this expression, for particular values of $\mathbf{k}$, would show Bragg peaks, and thus would be able to distinguish between a crystalline and a liquid phase of matter. But the amorphous solid state is different in that there is no constructive long-range order. This construct, therefore, is unable to diagnose the amorphous solid state.

A remedy for this situation presents itself immediately – we must, instead of the object (2.4), consider

$$\frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{N} \left| \langle \exp(i\mathbf{k}\cdot\mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle \right|^2. \tag{2.5}$$

$|\langle \exp(i\mathbf{k}\cdot\mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle|^2$ would be real and positive for any localized atom and thus the object (2.5 would be an order parameter suitable for studying the amorphous solidification transition. In fact, in turns out to be useful to define as our order parameter, in anticipation of the appearance of a replica field theory, a more general object, first presented in ref. [4], viz.,

$$\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m}) = \left[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\prod_{\alpha=1}^{n}\Big\langle \exp(-i\mathbf{k}^{\alpha}\cdot\mathbf{c}_j)\,Y^{*}_{\ell^{\alpha}m^{\alpha}}(\mathbf{s}_{j,a})\Big\rangle\right], \tag{2.6}$$

where the angle brackets $\langle\cdots\rangle$ (with no subscripts) indicate a statistical-mechanical ensemble average over configurations of the particles, subject to a given collection of permanent random constraints (i.e. bonds), and the square brackets $[\cdots]$ indicate an average over realizations of the bonds. This order parameter, which involves products of replicas of a single ensemble average, depends on the collections of wave vectors $\{\mathbf{k}^{\alpha}\}_{\alpha=1}^{n}$ and angular momentum indices $\{\ell^{\alpha},m^{\alpha}\}_{\alpha=1}^{n}$, which we collectively denote $\hat{\mathbf{k}}$ and $\hat{\ell}$, $\hat{m}$.

Let us examine this order parameter, first in order to ascertain the nature of the physical states that it is capable of diagnosing, and then to understand the type of statistical information that it encodes.

2.2.1 Detection of random positional and orientational localization

Consider the order parameter given by Eq. (2.6), and suppose that we elect to set $\ell^{\alpha}=0$ (for $\alpha=1,\ldots,n$). Then the order parameter becomes, up to insignificant factors of 4π:

$$\left[\frac{1}{N}\sum_{j=1}^{N}\prod_{\alpha=1}^{n}\Big\langle \exp(-i\mathbf{k}^{\alpha}\cdot\mathbf{c}_j)\Big\rangle\right]. \tag{2.7}$$

As discussed in detail, e.g., in Ref. [7], and also below in Sec. 4.4, these components of the order parameter are capable of detecting the spontaneous random freezing of particle positions (without regard to the behavior of the orbital orientations). More specifically, via the wave vector dependence, these order parameter components yield information about the fraction of particles that are positionally localized, as well as the statistical distribution of their positional localization lengths.

Suppose, instead, that we set $\mathbf{k}^\alpha = \mathbf{0}$ (for $\alpha = 1, \ldots, n$) in Eq. (2.6). Then the order parameter becomes

$$\left[\frac{1}{N} \sum_{j=1}^{N} \frac{1}{A} \sum_{a=1}^{A} \prod_{\alpha=1}^{n} \left\langle Y^*_{\ell^\alpha m^\alpha}(\mathbf{s}_{j,a}) \right\rangle \right]. \tag{2.8}$$

As discussed, e.g., in Refs. [4, 10], and also below in Sec. 4.5.2, this component of the order parameter is capable of detecting the spontaneous random freezing of orbital orientations (without regard to the behavior of the particle positions). More specifically, via its dependence on the angular indices $\{\ell^\alpha, m^\alpha\}_{\alpha=1}^{n}$, this order parameter yields information about the extent and character of the orientational localization of the orbitals. It is via this component of the order parameter that the most direct contact is made with the Edwards-Anderson order parameter for Heisenberg spin glasses, which detects the random orientational freezing of magnetic moments. For example, choosing $\{\ell^1, \ldots, \ell^n\} = \{1, 1, 0, \ldots, 0\}$, and contracting appropriately on m^1 and m^2 we obtain

$$\begin{aligned} \sum_{m^1, m^2 = -1}^{1} (-1)^{m^1} \delta_{m^1+m^2,0} &\left[\frac{1}{N} \sum_{j=1}^{N} \frac{1}{A} \sum_{a=1}^{A} \left\langle Y^*_{1m^1}(\mathbf{s}_{j,a}) \right\rangle \left\langle Y^*_{1m^2}(\mathbf{s}_{j,a}) \right\rangle \right] \\ &= \frac{3}{4\pi} \left[\frac{1}{N} \sum_{j=1}^{N} \frac{1}{A} \sum_{a=1}^{A} \left\langle \mathbf{s}_{j,a} \right\rangle \cdot \left\langle \mathbf{s}_{j,a} \right\rangle \right], \end{aligned} \tag{2.9}$$

thus recovering the familiar (vector) Edwards-Anderson form. More generally, the order parameter for random networks exhibits the unconventional features that the index ℓ can be greater than unity (so that higher multipole moments of the distribution of orientations can be accessed), as well as that a full characterization of the orientational freezing requires information from components with more than the familiar pair of thermal expectation values.

The third category of information results from examining the components of the order parameter corresponding to simultaneously nonzero values of both $\{\mathbf{k}^\alpha\}_{\alpha=1}^{n}$ and $\{\ell^\alpha\}_{\alpha=1}^{n}$. First, consider the subcase for which in every replica α at most one of ℓ^α and $\mathbf{k}^\alpha$ is nonzero. An example of such an order parameter component is

$$\left[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\Big\langle\exp(-i\mathbf{k}^1\cdot\mathbf{c}_j)\Big\rangle\Big\langle\exp(-i\mathbf{k}^2\cdot\mathbf{c}_j)\Big\rangle\Big\langle Y^*_{\ell^3m^3}(\mathbf{s}_{j,a})\Big\rangle\Big\langle Y^*_{\ell^4m^4}(\mathbf{s}_{j,a})\Big\rangle\right]. \tag{2.10}$$

Such components measure the statistical correlations between the strengths of positional and angular localization across the sample. *Inter alia*, such components address the question: if a certain particle is strongly localized positionally, how likely are the attached orbitals to be strongly localized orientationally?

Next, consider the general case in which some replicas α have nonzero values for both $\mathbf{k}^\alpha$ and ℓ^α. Such components provide information on the extent to which positional and orientational *thermal* fluctuations are correlated. For example, as is discussed in more detail below, by setting $\mathbf{k}^\alpha = \mathbf{0}$ in all replicas α except replicas 1 and 2, and by also setting $\ell^1 = \ell^2 = 1, m^1 = m^2 = 0$, and $\ell^\alpha = m^\alpha = 0$ in the remaining replicas α, we would obtain access to the disorder average of the quantity

$$\Big\langle(\mathbf{c}_j - \langle\mathbf{c}_j\rangle)(\mathbf{s}_{j,a} - \langle\mathbf{s}_{j,a}\rangle)_z\Big\rangle\cdot\Big\langle(\mathbf{c}_j - \langle\mathbf{c}_j\rangle)(\mathbf{s}_{j,a} - \langle\mathbf{s}_{j,a}\rangle)_z\Big\rangle, \tag{2.11}$$

which is a direct measure of the extent of the above-mentioned position-orientation fluctuation correlations.

Let us pause to emphasize the three levels of randomness presented by random network forming media. There is *thermal* randomness, by which we mean the thermal motion of the particle positions and orbital orientations. Then there is *architectural* randomness, resulting from the random manner in which covalent bonds are formed. Finally, there is *microstructural* randomness, i.e., the heterogeneity of the emergent solid state. This last level of randomness we capture statistically in terms of a joint probability distribution that characterizes the nature of the thermal motions.

2.2.2 Isolating the fraction of positionally localized particles

The most basic piece of information describing the amorphous solid state is the value of the fraction q of the N particles that are localized positionally, regardless of the value of their localization lengths and the angular localization of the orbitals attached to them. As shown in Refs. [4, 7], this fraction q can be accessed via the order parameter (2.6) in the following way: set $\ell^\alpha = m^\alpha = 0$ (for $\alpha = 1, \ldots, n$) and then pass to the limit $\hat{\mathbf{k}} \to \hat{\mathbf{0}}$ via a sequence for which $\sum_{\alpha=1}^{n} \mathbf{k}^\alpha = \mathbf{0}$. The resulting quantity *is* the fraction q. The reason for this is that whereas the value of $\langle \exp(-i\mathbf{k} \cdot \mathbf{c}_j) \rangle$ at $\mathbf{k} = \mathbf{0}$ is strictly unity, the limiting value of $\langle \exp(-i\mathbf{k} \cdot \mathbf{c}_j) \rangle$ (as $\mathbf{k} \to \mathbf{0}$) is a complex number of unit magnitude for positionally localized particles, but zero for delocalized particles. Thus, selecting a particular choice for the sequence of $\hat{\mathbf{k}}$ corresponding to $\mathbf{k}^1 = \mathbf{k}$ and $\mathbf{k}^2 = -\mathbf{k}$ we see that

$$lim_{\mathbf{k}\to\mathbf{0}} \frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{N} \left| \langle \exp(i\mathbf{k} \cdot \mathbf{c}_j) Y_{\ell m}(s_{j,a}) \rangle \right|^2 = q \tag{2.12}$$

For the sake of convenience, we shall refer to the localized fraction q as the solid fraction, and the delocalized fraction $1 - q$ as the liquid fraction.

2.2.3 Distribution of positional and orientational localization characteristics

To further elucidate the physical information regarding the positional and orientational localization of the particles and orbitals contained in the order parameter, we now present a form for the order parameter (2.6) that would be more amenable to interpreting the physical information that it encodes. To do so, we shall cast it in terms of certain *localizational characteristics*—quantities that describe the positional and orientational localization of particles and orbitals.



Figure 2.2 Positional localization of particles. The characteristic extent of the thermal fluctuations of the position of the particle is represented by the gray circle and measured by the localization length ξ.

We begin by considering the contribution to the order parameter (2.6) from a single particle j and a single orbital a attached to it, i.e., the expectation value

$$\left\langle e^{-i\mathbf{k}\cdot\mathbf{c}_j}\, Y^*_{\ell m}(\mathbf{s}_{j,a})\right\rangle. \tag{2.13}$$

This function is the *characteristic function* (i.e., the harmonic transform) of the joint probability distribution of the equilibrium positions of particle j and orientations of the attached orbital a, including correlations between the thermal fluctuations of this position and orientation. First, we consider the $(1-q)N$ particles in the delocalized fraction. For such particles we have, on the grounds of homogeneity, isotropy, and normalization, $\langle e^{-i\mathbf{k}\cdot\mathbf{c}_j}\, Y^*_{\ell m}(\mathbf{s}_{j,a})\rangle = (4\pi)^{-1/2}\,\delta_{\mathbf{k},\mathbf{0}}\,\delta_{\ell,0}\,\delta_{m,0}$. For the remaining qN localized particles we first extract from the expectation value (2.13) the phase factor associated with the mean position $\mu_j \equiv \langle \mathbf{c}_j\rangle$ of the particle, to obtain $e^{-i\mathbf{k}\cdot\mu_j}\langle e^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)}\, Y^*_{\ell m}(\mathbf{s}_{j,a})\rangle$, and then express the resulting quantity in terms of disconnected and connected (i.e., average and fluctuation) pieces:

$$\begin{aligned}\left\langle e^{-i\mathbf{k}\cdot\mathbf{c}_j}\, Y^*_{\ell m}(\mathbf{s}_{j,a})\right\rangle &= e^{-i\mathbf{k}\cdot\mu_j}\left\{\left\langle e^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)}\right\rangle \left\langle Y^*_{\ell m}(\mathbf{s}_{j,a})\right\rangle\right.\\ &\quad \left.+\left\langle\left(e^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)} - \langle e^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)}\rangle\right)\left(Y^*_{\ell m}(\mathbf{s}_{j,a}) - \langle Y^*_{\ell m}(\mathbf{s}_{j,a})\rangle\right)\right\rangle\right\}.\end{aligned} \tag{2.14}$$



Figure 2.3 Orientational localization of orbitals. The orientation of the orbital fluctuates thermally about its most probable value (broken line), the characteristic scale of these fluctuations being represented by the gray cone.

On the right hand side of this expression, the disconnected (i.e., the first) piece contains two factors: (i) $\langle \exp\left(-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)\right)\rangle$, which describes the positional localization of the particle (see Fig. 2.2); and (ii) $\langle Y^*_{\ell m}(\mathbf{s}_{j,a})\rangle$, which describes the orientational localization of the orbital (see Fig. 2.3). If we approximate the first factor in the connected piece by making use of the standard cumulant expansion, by letting $3\xi_j^2$ denote the (finite) mean square fluctuations $\langle\,(\mathbf{c}_j-\langle\mathbf{c}_j\rangle)\cdot(\mathbf{c}_j-\langle\mathbf{c}_j\rangle)\,\rangle$ in the position of the particle, and by following this strategy to second order, then we arrive at the approximation

$$\Big\langle \exp\left(-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)\right)\Big\rangle \approx \exp(-k^2\xi_j^2/2). \tag{2.15}$$

As for the connected (i.e., the second) term on the right-hand side of Eq. (2.14), it describes correlations between the fluctuations in the particle position and the orbital orientation (see Fig. 2.4). In the same way that we have introduced the diagnostic ξ to characterize positional localization, we now introduce two further diagnostics, Σ and Γ, via:

$$\Sigma_{\ell m;j,a} \equiv \Big\langle Y^*_{\ell m}(\mathbf{s}_{j,a})\Big\rangle, \tag{2.16}$$

$$\mathrm{e}^{-|\mathbf{k}|^2\xi_j^2/2}\Gamma_{\ell m;j,a}(\mathbf{k}) \equiv \Big\langle(\mathrm{e}^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)}-\langle\mathrm{e}^{-i\mathbf{k}\cdot(\mathbf{c}_j-\mu_j)}\rangle)(Y^*_{\ell m}(\mathbf{s}_{j,a})-\langle Y^*_{\ell m}(\mathbf{s}_{j,a})\rangle)\Big\rangle \tag{2.17}$$



Figure 2.4 Orientational-positional thermal fluctuation correlations. Imagine that the particle is connected to a rather immobile particle by the top left orbital. As the particle moves to the shaded position its orbitals reorient accordingly.

The collection of complex-valued numbers $\{\Sigma_{\ell m;j,a}\}$ characterizes the orientational localization of orbital a on particle j; the collection of complex-valued functions $\{\Gamma_{\ell m;j,a}(\mathbf{k})\}$ characterizes the correlations between the thermal fluctuations in the position of particle j and the orientation of orbital a attached to it. For example, consider $\Gamma_{10;j,a}(\mathbf{k})$. By expanding the exponential to first order (as we shall establish later, typical values of k are small near the transition), and recalling that (up to numerical factors) $Y_{10}(\mathbf{s})$ is s_z, we see that

$$\mathrm{e}^{-|\mathbf{k}|^2\xi_j^2/2}\,\Gamma_{10;j,a}(\mathbf{k}) = -i\sqrt{\frac{3}{4\pi}}\;\mathbf{k}\cdot\Big\langle\Big((\mathbf{c}_j-\mu_j)-\langle\mathbf{c}_j-\mu_j\rangle\Big)\Big((s_{j,a})_z-\langle(s_{j,a})_z\rangle\Big)\Big\rangle+\mathcal{O}(\mathbf{k}^2), \tag{2.18}$$

which does indeed measure correlations between the positional and orientational thermal fluctuations, in accordance with the discussion of this component of the order-parameter, given at the end of Sec. 2.2.1.

By rewriting Eq. (2.14) in terms of these diagnostics, and making use of the approximation (2.15), we arrive at the form

$$\Big\langle\mathrm{e}^{-i\mathbf{k}\cdot\mathbf{c}_j}\,Y^*_{\ell m}(\mathbf{s}_{j,a})\Big\rangle\approx\mathrm{e}^{-i\mathbf{k}\cdot\mu_j}\,\mathrm{e}^{-|\mathbf{k}|^2\xi_j^2/2}\Big\{\Sigma_{\ell m;j,a}+\Gamma_{\ell m;j,a}(\mathbf{k})\Big\}. \tag{2.19}$$

By inserting this form, appropriate for particles j that comprise the localized fraction, into Eq. (2.6), and incorporating the contribution from the delocalized fraction, we arrive at the following form for the order parameter:

$$
\begin{aligned}
&\left[\frac{1}{N} \sum_{j=1}^{N} \frac{1}{A} \sum_{a=1}^{A} \prod_{\alpha=1}^{n} \left\langle \mathrm{e}^{-i\mathbf{k}^\alpha \cdot \mathbf{c}_j} \, Y^*_{\ell^\alpha m^\alpha}(\mathbf{s}_{j,a}) \right\rangle \right] \\
&\approx (1-q) \prod_{\alpha=1}^{n} \delta_{\mathbf{k}^\alpha,\mathbf{0}} \delta_{\ell^\alpha,0} \delta_{m^\alpha,0} \\
&\qquad + \left[\frac{1}{N} \sum_{j\,\mathrm{loc.}} \frac{1}{A} \sum_{a=1}^{A} \prod_{\alpha=1}^{n} \mathrm{e}^{-i\mathbf{k}^\alpha \cdot \mu_j} \, \mathrm{e}^{-|\mathbf{k}^\alpha|^2 \xi_j^2/2} \Big(\Sigma_{\ell^\alpha m^\alpha;j,a} + \Gamma_{\ell^\alpha m^\alpha;j,a}(\mathbf{k}^\alpha) \Big) \right] \\
&= (1-q) \prod_{\alpha=1}^{n} \delta_{\mathbf{k}^\alpha,\mathbf{0}} \delta_{\ell^\alpha,0} \delta_{m^\alpha,0} + q \int d^3\mu \int d\tau \, d\{\Sigma\} \, \mathcal{D}\{\Gamma\} \, P(\mu, \tau, \{\Sigma\}, \{\Gamma\}) \\
&\qquad \times \mathrm{e}^{-i\mu \cdot \sum_{\alpha=1}^{n} \mathbf{k}^\alpha} \, \mathrm{e}^{-\frac{1}{2\tau} \sum_{\alpha=1}^{n} |\mathbf{k}^\alpha|^2} \prod_{\alpha=1}^{n} \{ \Sigma_{\ell^\alpha m^\alpha;j,a} + \Gamma_{\ell^\alpha m^\alpha;j,a}(\mathbf{k}^\alpha) \}, \qquad (2.20)
\end{aligned}
$$

where we have made the convenient definition $\tau \equiv 1/\xi^2$. The notation $\sum_{j\mathrm{loc.}}$ denotes a sum over all particles comprising the localized (solid) fraction. The integration measures $d\{\Sigma\}$ and $\mathcal{D}\{\Gamma\}$ respectively denote the multiple measure $\prod_{\ell m} d\Sigma_{\ell m}$ and the multiple functional measure $\prod_{\ell m} \mathcal{D}\Gamma_{\ell m}$. We have also introduced the joint probability distribution P, central to our characterization of the localized particles in amorphous solid state, defined via

$$
\begin{aligned}
&P(\mu, \tau, \{\Sigma\}, \{\Gamma\}) \equiv \\
&\quad \left[\frac{1}{N} \sum_{j=1}^{N} \frac{1}{A} \sum_{a=1}^{A} \delta(\mu - \mu_j) \, \delta(\tau - \xi_j^{-2}) \prod_{\ell=0}^{\infty} \prod_{m=-\ell}^{\ell} \delta(\Sigma_{\ell m} - \Sigma_{\ell m;j,a}) \, D(\Gamma_{\ell m} - \Gamma_{\ell m;j,a}) \right], \qquad (2.21)
\end{aligned}
$$

in which the final factor $D(\cdot)$ is a functional delta-function associated with the dependence of Γ on the continuous "index" $\hat{\mathbf{k}}$.

The next step in our construction of a physically motivated form for the order parameter involves the identification of specific symmetries that we anticipate the amorphous solid state to possess, viz., macroscopic translational invariance (MTI) and macroscopic rotational invariance (MRI). MTI reflects the notion that although in the amorphous solid state translational invariance is spontaneously broken at the microscopic level (in any particular realization of the disorder), this invariance is restored at the macroscopic level, in the sense that no quantity computed by averaging over any macroscopic subvolume of the system is expected to exhibit any dependence on the particular subvolume chosen. Similarly, MRI reflects the notion that although rotational invariance is spontaneously broken at the microscopic level, it is restored at the macroscopic level in the sense that no quantity computed by averaging over any macroscopic subvolume of the system is expected to exhibit any orientational preference.

As for MTI, it amounts to the hypotheses: (i) that the disorder-averaged distribution P exhibits no correlation between the mean location of a particle and its other statistical characteristics; and (ii) that the distribution is translationally invariant (i.e., is independent of μ).

Although MRI also imposes conditions on the joint probability distribution P, we do not need to impose these conditions explicitly. The reason for that is that MRI for the component $\Omega(\hat{\mathbf{k}}; \hat{0}, \hat{0})$ is assured by the fact that $\Sigma_{00;j,a}$ and $\Gamma_{00;j,a}(\hat{\mathbf{k}})$ are constants (in fact, one is zero), and the assumption that the localization clouds of the particles are spherical and, accordingly, described by the single r.m.s. value of the fluctuation in the particle's position, viz., $3\xi_j^2$. MRI for the anisotropic components of $\Omega(\hat{\mathbf{k}}; \hat{\ell}, \hat{m})$ is a consequence of the fact that they, as we shall see below, are perturbed away from their zero values by MRI-maintaining couplings to the $\Omega(\hat{\mathbf{k}}; \hat{0}, \hat{0})$ component. Thus, MRI is assured by the theory itself, and does not need to be explicitly incorporated into the proposed form of the order parameter.

By making use of the MTI hypotheses we arrive at the form:

$$P(\mu, \tau, \{\Sigma\}, \{\Gamma\}) = \frac{1}{V} P(\tau, \{\Sigma\}, \{\Gamma\}), \tag{2.22}$$

which, when inserted into Eq. (2.20), leads to the expression

$$
\begin{aligned}
&(4\pi)^{n/2}\,\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})\Big|_{\mathbf{k}^0=\mathbf{0},\ell^0=m^0=0} = \\
&(1-q)\prod_{\alpha=1}^{n}\delta_{\mathbf{k}^\alpha,\mathbf{0}}\,\delta_{\ell^\alpha,0}\,\delta_{m^\alpha,0} + q\,\delta_{\sum_{\alpha=1}^{n}\mathbf{k}^\alpha,\mathbf{0}}\int_0^\infty d\tau\int d\{\Sigma\}\,\mathcal{D}\{\Gamma\}\,P(\tau,\{\Sigma\},\{\Gamma\}) \\
&\qquad\times \mathrm{e}^{-\frac{1}{2\tau}\sum_{\alpha=0}^{n}|\mathbf{k}^\alpha|^2}\prod_{\alpha=0}^{n}\{\Sigma_{\ell^\alpha m^\alpha;j,a}+\Gamma_{\ell^\alpha m^\alpha;j,a}(\mathbf{k}^\alpha)\},
\end{aligned}
\tag{2.23}
$$

where we have introduced the notation $\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})|_{\mathbf{k}^0=\mathbf{0},\ell^0=m^0=0}$ to denote the order parameter (2.6), and we remind ourselves that hats indicate $(n+1)$-fold replicated versions of quantities (e.g., $\hat{\mathbf{k}}$ represents $(\mathbf{k}^0,\mathbf{k}^1,\ldots,\mathbf{k}^n)$). By extending the result of this approach to include the dependence of the order parameter on the zero-replica variables $(\mathbf{k}^0,\ell^0,m^0)$ in a permutation-symmetry–dictated way we arrive at the form

$$
\begin{aligned}
&(4\pi)^{(n+1)/2}\,\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m}) = (1-q)\prod_{\alpha=0}^{n}\delta_{\mathbf{k}^\alpha,\mathbf{0}}\,\delta_{\ell^\alpha,0}\,\delta_{m^\alpha,0} \\
&+q\delta_{\tilde{\mathbf{k}},\mathbf{0}}\int_0^\infty d\tau\int d\{\Sigma\}\,\mathcal{D}\{\Gamma\}\,p(\tau,\{\Sigma\},\{\Gamma\})\,\mathrm{e}^{-\hat{\mathbf{k}}^2/2\tau}\prod_{\alpha=0}^{n}\{\Sigma_{\ell^\alpha m^\alpha;j,a}+\Gamma_{\ell^\alpha m^\alpha;j,a}(\mathbf{k}^\alpha)\}.
\end{aligned}
\tag{2.24}
$$

As we shall see below, for our solution we shall need an assumption for the form of the order-parameter component $\Omega(\hat{\mathbf{k}};\hat{0},\hat{0})$. To motivate this assumption, we set $\hat{\ell}=\hat{m}=\hat{0}$ in Eq. (2.24). As is easy to see from the definitions (2.16) and (2.17), $\Sigma_{00;j,a}=1/\sqrt{4\pi}$ and $\Gamma_{00;j,a}=0$, leaving us with the form

$$
(4\pi)^{(n+1)/2}\,\Omega(\hat{\mathbf{k}};\hat{0},\hat{0}) = (1-q)\prod_{\alpha=0}^{n}\delta_{\mathbf{k}^\alpha,\mathbf{0}} + q\,\delta_{\tilde{\mathbf{k}},\mathbf{0}}\int_0^\infty d\tau\,p(\tau)\,\mathrm{e}^{-\hat{\mathbf{k}}^2/2\tau},
\tag{2.25}
$$

where $p(\tau)$ is the reduced form of the full joint probability distribution $P(\tau,\{\Sigma\},\{\Gamma\})$ that describes only the positional localization of the particles:

$$
p(\tau)\equiv\int d\{\Sigma\}\,\mathcal{D}\{\Gamma\}\,P(\tau,\{\Sigma\},\{\Gamma\}).
\tag{2.26}
$$

We note that, up to trivial factors of 4π, the expression (2.25) is identical to the Ansatz used in Refs. [7, 6] in the context of vulcanized macromolecular media.

CHAPTER 3

STATISTICAL MECHANICS OF THE MODEL

3.1 Disorder-Averaging; Replica Statistical Mechanics

Having described the relevant "kinematics," i.e., the degrees of freedom and the constraints that characterize the model of randomly covalently bonded particles, we now formulate the statistical mechanics of the system, paying particular attention to the quenched (i.e., nonequilibrating) nature of the random constraints. At this stage we shall be following the method sketched in Ref. [4], which itself builds upon the general approach to macromolecular networks introduced in Ref. [14].

3.1.1 Partition function

The partition function of the system, subject to the constraints $\{j_e, j'_e; a_e, a'_e\}_{e=1}^{M}$ (which we collectively denote by $\mathcal{C}$), relative to the partition function of the unconstrained system (that is, representing the change in free energy due to the introduction of crosslinks), is given by

$$\tilde{Z}(\mathcal{C}) = \Big\langle \prod_{e=1}^{M} \delta^{(3)}(\mathbf{c}_{j_e} + \frac{1}{2}\mathbf{s}_{j_e,a_e} - \mathbf{c}_{j'_e} - \frac{1}{2}\mathbf{s}_{j'_e,a'_e})\,\Delta^{(2)}(\mathbf{s}_{j_e,a_e} + \mathbf{s}_{j'_e,a'_e})\Big\rangle_{N,1}. \tag{3.1}$$

The angle brackets denote equilibrium averaging with respect to a Hamiltonian that incorporates interactions between distinct particles, as well as between the orbitals of a single particle. The subscript indicates that this average is taken over one copy of a system of N particles, and anticipates the introduction of replicas that we shall make shortly. The two types of delta-function, $\delta^{(3)}$ and $\Delta^{(2)}$, serve to eliminate configurations that fail to satisfy the constraints discussed in Sec. 2.1, and are appropriately defined in the following way:

$$\delta^{(3)}(\mathbf{c}_1 - \mathbf{c}_2) = \delta^{(3)}(\mathbf{c}_2 - \mathbf{c}_1) \equiv \sum_{\mathbf{k}} \left(\frac{\exp i\mathbf{k}\cdot\mathbf{c}_1}{\sqrt{V}}\right)\left(\frac{\exp i\mathbf{k}\cdot\mathbf{c}_2}{\sqrt{V}}\right)^*, \tag{3.2}$$

$$\Delta^{(2)}(\mathbf{s}_1, \mathbf{s}_2) = \Delta^{(2)}(\mathbf{s}_2, \mathbf{s}_1) \equiv \sum_{\ell=0}^{\infty}\sum_{m=-\ell}^{\ell} Y_{\ell m}(\mathbf{s}_1)\, Y^*_{\ell m}(\mathbf{s}_2), \tag{3.3}$$

where, corresponding to the periodic boundary conditions imposed on the system, the sum over $\mathbf{k}$ is taken over the Cartesian components $k_\nu = 2\pi n_\nu / V^{1/3}$ (with n_ν being integers, both positive and negative). The $Y_{\ell m}$ are the usual spherical harmonic functions, the arguments of which are unit vectors, describing orbital orientations. As can be readily checked by making use of the orthonormality properties of the harmonic functions (see app. A.1), the delta-functions possess the usual properties:

$$\int_V d^3\mathbf{c}_2 \delta^3(\mathbf{c}_1 - \mathbf{c}_2)\, \delta^3(\mathbf{c}_2 - \mathbf{c}_3) = \delta^3(\mathbf{c}_1 - \mathbf{c}_3) \tag{3.4}$$

$$\int_S d^2\mathbf{s}_2 \Delta^{(2)}(\mathbf{s}_1, \mathbf{s}_2)\, \Delta^{(2)}(\mathbf{s}_2, \mathbf{s}_3) = \Delta^{(2)}(\mathbf{s}_1, \mathbf{s}_3). \tag{3.5}$$

Strictly speaking, the partition function $\tilde{Z}$ is correct only up to the appropriate Gibbs factorial factor, and would not, as it stands, give rise to an extensive free energy (hence the tilde). As we shall be focusing on the order-parameter self-consistency equation, in which (as is well known) the Gibbs factor plays no role, this awkward factor can be safely omitted here. For a detailed discussion of this issue, see Sec. 2.4 of Ref. [7].

3.1.2 Deam-Edwards distribution

At this stage, we introduce a statistical distribution characterizing the realization of the random bonds. To do this, we shall invoke an elaboration [4] of the elegant strategy of Deam and Edwards [14], introduced in the context of vulcanized macromolecular media.

We take for the probability density that the collection of bonds $\mathcal{C}$ is formed the quantity

$$\mathcal{P}_M(\mathcal{C}) \propto \frac{(2\pi V\mu^2/NA^2)^M}{M!}\,\tilde{Z}(\mathcal{C}), \tag{3.6}$$

Rather than work with a fixed number of bonds, we allow their number to vary in a quasi-Poissonian way, and instead control the *mean* number of bonds by the control parameter μ^2.

What is the physical content of this Deam-Edwards-like distribution? For a given value of M, the distribution is proportional to the probability density for finding the set of pairs of orbitals $\{j_m, j'_m; a_m, a'_m\}_{m=1}^{M}$ to be overlapping, so that it is geometrically possible for a (permanent) chemical bond to be formed between them. The factor μ^{2M} represents the probability that a bond actually is formed between each of these M overlapping pairs. Thus, the Deam-Edwards distribution provides a statistical characterization of a process of forming permanent bonds in which constraints are instantaneously introduced into the liquid state at equilibrium. As such, it is an idealization of the random-network-forming process, which generally takes place on a time-scale during which at least some relaxation of the structure can occur. To handle the complication of relaxation would require the introduction of kinetics into the description, rather than purely equilibrium notions. Said another way, one can view the Deam-Edwards distribution as a strategy for freezing in liquid-state correlations, as process that is regarded as happening spontaneously in glass-forming systems, but here is introduced externally. The distribution encodes the physically attractive feature that the networks it gives appreciable weight to exhibit the macroscopic symmetries of the liquid state (namely MTI and MRI), inasmuch as the bond collections to which it gives appreciable weight correspond to likely configurations of the liquid state. With this distribution of bonds some of the structure of the liquid state is *quenched in*; the extent of this quenching in is controlled by the mean number of bonds formed.

3.1.3 Replica representation of the disorder-averaged free energy

We now set about constructing the disorder-averaged free energy per particle (relative to that of the system prior to random covalent bonding, i.e., the difference between the free energy per particle in the crosslinked and uncrosslinked states) f, which is defined via

$$N\beta f \equiv [\ln \tilde{Z}(\mathcal{C})], \tag{3.7}$$

where $\beta(\equiv 1/k_{\mathrm{B}}T)$ measures the inverse temperature. [1] As mentioned in the previous subsection, the Gibbs combinatorial factor has been omitted, but this will have no consequences for the order-parameter self-consistent equation. By making use of the replica technique (see, e.g., Ref. [3]), f can be obtained via:

$$\begin{aligned} f &= \lim_{n\to 0} f_n, & (3.8)\\ -n\beta N f_n &\equiv [\tilde{Z}^n] - 1 = \left(\mathcal{Z}_{n+1} - \mathcal{Z}_1\right)/\mathcal{Z}_1, & (3.9)\\ \mathcal{Z}_{n+1} &\equiv \Bigg\langle \exp\Bigg(\frac{2\pi V\mu^2}{NA^2}\sum_{j,j'=1}^{N}\sum_{a,a'=1}^{A}\prod_{\alpha=0}^{n}\delta^{(3)}(\mathbf{c}_j^\alpha + \tfrac{1}{2}\mathbf{s}_{j,a}^\alpha - \mathbf{c}_{j'}^\alpha - \tfrac{1}{2}\mathbf{s}_{j',a'}^\alpha) \\ &\qquad \times \Delta^{(2)}(\mathbf{s}_{j,a}^\alpha, -\mathbf{s}_{j',a'}^\alpha)\Bigg)\Bigg\rangle_{N,n+1}. & (3.10)\end{aligned}$$

Here, $\mathcal{Z}_{n+1}$ is the replicated partition function, arising from the averaging of $\tilde{Z}^n$ over the Deam-Edwards–type distribution (3.6), and the denominator $\mathcal{Z}_1$ arises from the normalization of the Deam-Edwards distribution (see App. B.1) for details). Notice the striking occurrence of a theory involving $n+1$, rather than the usual n, replicas, a feature, arising from the presence in the partition function in the Deam-Edwards distribution. (The extra replica "computes" the distribution of quenched random bonds.) The angle brackets $\langle\cdots\rangle_{N,n+1}$ indicate an $n+1$-fold replicated normalized average over the positions of the

[1] On the right-hand side of Eq. (3.7) β appears in the partition fucntion via the angle brackets $\langle\cdots\rangle$, which denote thermal averaging. Any quantity thus averaged will exhibit temperature dependence.

particles and the orientations of the orbitals, weighted suitably by a Hamiltonian that does not couple the replicas.

As one can see from the exponent in Eq. (3.10), the replicated theory possesses the symmetries of independent translations and rotations of the replicas, i.e.,

$$\mathbf{c}^{\alpha} \rightarrow \mathcal{R}^{\alpha} \cdot \mathbf{c}^{\alpha} + \mathbf{a}^{\alpha}, \tag{3.11}$$

$$\mathbf{s}_a^{\alpha} \rightarrow \mathcal{R}^{\alpha} \cdot \mathbf{s}_a^{\alpha}, \tag{3.12}$$

where $\{\mathbf{a}^{\alpha}\}_{\alpha=0}^{n}$ are $n+1$ independent arbitrary translation 3-vectors, and $\{\mathcal{R}^{\alpha}\}_{\alpha=0}^{n}$ are $n+1$ independent arbitrary 3-by-3 rotation matrices. As we shall see, the transition to the amorphous solid state is marked by the spontaneous breaking of the symmetries of the relative translations and rotations of the replicas; the common translations and rotations remain as residual symmetries. These residual symmetries correspond to the macroscopic translational and rotational symmetry of the amorphous solid state discussed in Sec. 2.2.3. The theory also possesses the symmetry of the permutation of the $n+1$ replicas, which remains intact in the amorphous solid state.

For the sake of convenience, we introduce the replicated delta-functions, defined by

$$\hat{\delta}(\hat{\mathbf{c}}_1 - \hat{\mathbf{c}}_2) \equiv \prod\nolimits_{\alpha=0}^{n} \delta^{(3)}(\mathbf{c}_2^{\alpha} - \mathbf{c}_3^{\alpha}), \tag{3.13}$$

$$\hat{\Delta}(\hat{\mathbf{s}}_1, \hat{\mathbf{s}}_2) \equiv \prod\nolimits_{\alpha=0}^{n} \Delta^{(2)}(\mathbf{s}_1^{\alpha}, \mathbf{s}_2^{\alpha}), \tag{3.14}$$

where $\hat{\mathbf{c}}$ denotes $\{\mathbf{c}^0, \mathbf{c}^1, \ldots, \mathbf{c}^n\}$ and $\hat{\mathbf{s}}$ denotes $\{\mathbf{s}^0, \mathbf{s}^1, \ldots, \mathbf{s}^n\}$.

The latter delta-function has two symmetry properties that we shall be making use of:

$$\begin{aligned} \hat{\Delta}(\hat{\mathbf{s}}_1, \hat{\mathbf{s}}_2) &= \hat{\Delta}(\hat{\mathbf{s}}_2, \hat{\mathbf{s}}_1), \\ \hat{\Delta}(\hat{\mathbf{s}}_1, \hat{\mathbf{s}}_2) &= \hat{\Delta}(-\hat{\mathbf{s}}_1, -\hat{\mathbf{s}}_2), \end{aligned} \tag{3.15}$$

which can be easily checked by using the symmetry properties of the spherical harmonics $Y_{\ell m}$. We also introduce the replicated spherical harmonics $\hat{Y}$, defined by

$$\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}) \equiv \prod\nolimits_{\alpha=0}^{n} Y_{\ell^\alpha m^\alpha}(\mathbf{s}^\alpha), \tag{3.16}$$

where, as before, $\hat{\ell}$ and $\hat{m}$ respectively denote $\{\ell^0, \ell^1, \ldots, \ell^n\}$ and $\{m^0, m^1, \ldots, m^n\}$.

3.2 Mean-Field Approximation

3.2.1 Self-consistency condition for the order parameter

We now develop a mean-field approximation for the replica partition function, Eq. (3.10). To do this, we rewrite the partition function as follows:

$$\begin{aligned}
\mathcal{Z}_{n+1} &= \Big\langle \exp\Big(2\pi N V \mu^2 \int_V d\hat{c} \int_S d\hat{s}\, \frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{A} \hat{\delta}((\hat{\mathbf{c}}_j + \tfrac{1}{2}\hat{\mathbf{s}}_{j,a}) - \hat{\mathbf{c}})\, \hat{\Delta}(\hat{\mathbf{s}}_{j,a}, \hat{\mathbf{s}}) \\
&\qquad \times \frac{1}{NA} \sum_{j'=1}^{N} \sum_{a'=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_{j'} + \tfrac{1}{2}\hat{\mathbf{s}}_{j',a'}))\, \hat{\Delta}(\hat{\mathbf{s}}, -\hat{\mathbf{s}}_{j',a'})\Big)\Big\rangle_{N,n+1} && (3.17) \\
&= \Big\langle \exp\Big(2\pi N V \mu^2 \int_V d\hat{c} \int_S d\hat{s}\, \frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_j + \tfrac{1}{2}\hat{\mathbf{s}}_{j,a}))\, \hat{\Delta}(\hat{\mathbf{s}}, \hat{\mathbf{s}}_{j,a}) \\
&\qquad \times \frac{1}{NA} \sum_{j'=1}^{N} \sum_{a'=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_{j'} + \tfrac{1}{2}\hat{\mathbf{s}}_{j',a'}))\, \hat{\Delta}(-\hat{\mathbf{s}}, \hat{\mathbf{s}}_{j',a'})\Big)\Big\rangle_{N,n+1}, && (3.18)
\end{aligned}$$

where $\int_V d\hat{c}$ denotes $\prod_{\alpha=0}^{n} \int_V d^3\mathbf{c}^\alpha$, and $\int_S d\hat{s}$ denotes $\prod_{\alpha=0}^{n} \int_S d^2\mathbf{s}^\alpha$, and where, to obtain the last form, we have used the symmetry properties of the delta-functions (3.15).

Next, we introduce the (real-space version of the) amorphous solid order parameter,

$$\Omega(\hat{\mathbf{c}}; \hat{\mathbf{s}}) \equiv \Big\langle \frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_j + \tfrac{1}{2}\hat{\mathbf{s}}_{j,a}))\, \hat{\Delta}(\hat{\mathbf{s}}, \hat{\mathbf{s}}_{j,a}) \Big\rangle. \tag{3.19}$$

Then, upon setting

$$\frac{1}{NA} \sum_{j=1}^{N} \sum_{a=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_j + \tfrac{1}{2}\hat{\mathbf{s}}_{j,a}))\, \hat{\Delta}(\hat{\mathbf{s}}, \hat{\mathbf{s}}_{j,a}) = \Omega(\hat{\mathbf{c}}; \hat{\mathbf{s}}) + \delta\Omega(\hat{\mathbf{c}}; \hat{\mathbf{s}}), \tag{3.20}$$

i.e., expressing the microscopic variable in terms of its average value $\Omega(\hat{\mathbf{c}}, \hat{\mathbf{s}})$ plus the fluctuation $\delta\Omega(\hat{\mathbf{c}}; \hat{\mathbf{s}})$, expanding the exponent in powers of $\delta\Omega(\hat{\mathbf{c}}; \hat{\mathbf{s}})$, and omitting terms quadratic in $\delta\Omega(\hat{\mathbf{c}};\hat{\mathbf{s}})$ (which describe the fluctuation correlations), we obtain the mean-field approximation

$$\begin{aligned}\mathcal{Z}_{n+1} \approx \exp\Bigg\{ & -2\pi N V \mu^2 \int_V d\hat{c} \int_S d\hat{s}\, \Omega(\hat{\mathbf{c}};\hat{\mathbf{s}})\, \Omega(\hat{\mathbf{c}};-\hat{\mathbf{s}}) \\ & + N \ln \Bigg\langle \exp\Bigg(4\pi V \mu^2 \int_V d\hat{c} \int_S d\hat{s}\ \Omega(\hat{\mathbf{c}};-\hat{\mathbf{s}}) \\ & \times \frac{1}{A}\sum_{a=1}^{A} \hat{\delta}(\hat{\mathbf{c}} - (\hat{\mathbf{c}}_1 + \tfrac{1}{2}\hat{\mathbf{s}}_{1,a}))\, \hat{\Delta}(\hat{\mathbf{s}},\hat{\mathbf{s}}_{1,a}) \Bigg) \Bigg\rangle_{1,n+1} \Bigg\},\end{aligned} \tag{3.21}$$

where the resulting expectation value involves only the position and orbital-orientations of a single particle.

The reader will have observed that the mean-field approximation strategy has yielded a one-particle problem, Eq. (3.21), as desired. However, there is a subtlety associated with the manner in which the various interactions present in Eq. (3.18) are treated, which we now address. The angle brackets in Eq. (3.18) denote averaging over $n+1$ (coupled) replicas of the N (coupled) particle system. The intra-replica coupling originates in the interactions between particles present in the liquid state; on the other hand, the inter-replica coupling originates in the random constraints. As discussed in detail in Sec. 5.1 of Ref. [7], it is useful to transfer the so-called one-replica sector (that is, the sector where only one of the wavevectors $\mathbf{k}^\alpha$ is nonzero) contribution to the inter-replica coupling to the intra-replica coupling (which is thereby renormalized). The intra- and inter-replica couplings both contain trivial contributions in the zero-replica sector (that is, the sector corresponding to $\hat{\mathbf{k}} = \hat{0}$), as does the order parameter; we ignore these contributions. The subtlety is that the structure of the theory in the one-replica sector is quite different from that in the higher-replica sectors: whereas the constraints tend to destabilize *all* sectors, this tendency is counteracted only in the one-replica sector by the original intra-replica interactions. Consequently, at the amorphous solidification transition the one-replica sector component of the order parameter remains zero, whilst the higher-replica sector components become nonzero. Indeed, the competition between these two processes can be regarded as a form of frustration, which resolves itself by the formation of a state possessing MTI and MRI (see Sec. 2.2.3).

On a technical level, this discussion amounts to the following dictum: in all subsequent equations, e.g., Eqs. (3.21,3.22,3.25), the component of the order parameter lying in the one-replica sector is to be set to zero. Accordingly, the self-consistent equations that follow pertain to all sectors *except* the zero and one replica sectors. This notion is straightforward when the order parameter is expressed in the (plane and spherical) harmonic representation [as it is, e.g., in Eq. (3.25)]. In this representation, setting the one-replica sector contribution to zero refers to setting to zero the contribution in which nonzero entries in $\{\hat{\mathbf{k}};\hat{\ell},\hat{m}\}$ appear in precisely one replica. (By the zero-replica sector we mean the sector with $\hat{\mathbf{k}}=\hat{\ell}=\hat{m}=\hat{0}$.)

We now return to the task of obtaining a self-consistent equation for the order parameter. By making the partition function (3.21) stationary with respect to $\Omega(\hat{\mathbf{c}};\hat{\mathbf{s}})$ we arrive at self-consistent equation (SCE) for the order-parameter:

$$\Omega(\hat{\mathbf{c}}_0;\hat{\mathbf{s}}_0)=\frac{\begin{array}{l}\Big\langle \frac{1}{A}\sum_{a=1}^{A}\hat{\delta}(\hat{\mathbf{c}}_0-(\hat{\mathbf{c}}_1+\tfrac{1}{2}\hat{\mathbf{s}}_{1,a}))\,\hat{\Delta}(\hat{\mathbf{s}}_0,\hat{\mathbf{s}}_{1,a})\\ \quad\times\exp\left(4\pi V\mu^2\int_V d\hat{c}\int_S d\hat{s}\,\Omega(\hat{\mathbf{c}};-\hat{\mathbf{s}})\frac{1}{A}\sum_{a=1}^{A}\hat{\delta}(\hat{\mathbf{c}}-(\hat{\mathbf{c}}_1+\tfrac{1}{2}\hat{\mathbf{s}}_{1,a}))\,\hat{\Delta}(\hat{\mathbf{s}},\hat{\mathbf{s}}_{1,a})\right)\Big\rangle\end{array}}{\left\langle\exp\left(4\pi V\mu^2\int_V d\hat{c}\int_S d\hat{s}\,\Omega(\hat{\mathbf{c}};-\hat{\mathbf{s}})\frac{1}{A}\sum_{a=1}^{A}\hat{\delta}(\hat{\mathbf{c}}-(\hat{\mathbf{c}}_1+\tfrac{1}{2}\hat{\mathbf{s}}_{1,a}))\,\hat{\Delta}(\hat{\mathbf{s}},\hat{\mathbf{s}}_{1,a})\right)\right\rangle}. \tag{3.22}$$

The presence of $\hat{\Delta}$-function factors provides the option of replacing the dynamical variable $\hat{\mathbf{s}}_{1,a}$ in the argument of the δ-functions by the parametric variable $\hat{\mathbf{s}}$, which replacement we sometimes make.

The transformation of the order parameter to a representation in terms of the plane wave and spherical harmonic coordinates, and the inverse transformation, are effected as follows:

$$\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m}) = \int_S d\hat{s}\ \hat{Y}^*_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}})\ \exp(\tfrac{1}{2}i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}) \int_V d\hat{c}\ \exp(-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}})\,\Omega(\hat{\mathbf{c}};\hat{\mathbf{s}}), \tag{3.23}$$

$$\Omega(\hat{\mathbf{c}};\hat{\mathbf{s}}) = \frac{1}{V^{n+1}}\sum\nolimits_{\hat{\mathbf{k}}}\exp(i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}})\exp(-\tfrac{1}{2}i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}})\sum\nolimits_{\hat{\ell}\hat{m}}\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}})\,\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m}). \tag{3.24}$$

This nonstandard choice of transformation that incorporates factors of $\exp(\frac{1}{2}i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}})$ has the effect of keeping the physical interpretation of the order parameter $\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ free of any complicating factors of $\exp(\frac{1}{2}i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}})$, leaving the full factor $\exp(i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}})$ in the fluctuating variable to which the order parameter couples. Via this transformation, one arrives at a transformed self-consistent equation for the order parameter:

$$\Omega(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0) = \frac{\begin{aligned}&\Big\langle \frac{1}{A}\sum_{a=1}^{A} \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\,\hat{Y}^*_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_a)\\ &\times\exp\left(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}}\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\right)\Big\rangle_{1,n+1}\end{aligned}}{\Big\langle\exp\left(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}}\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\right)\Big\rangle_{1,n+1}}. \tag{3.25}$$

We shall often refer to the non-dummy-variable triple $(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0)$ as the "external variables."

3.2.2 Instability of the fluid state

We now demonstrate that upon increasing the density of formed bonds the fluid state is rendered linearly unstable. To do this we follow Ref. [10], and expand the replica free energy, $n\beta N f_n$ in Eq. (3.9), to second order in the order parameter Ω, thus obtaining

$$\begin{aligned} n\beta N f_n(\Omega) \approx\ & 2\pi\mu^2 NV\sum_{\hat{\mathbf{k}}}\sum_{\hat{\ell}_1,\hat{m}_1}\sum_{\hat{\ell}_2,\hat{m}_2}\Omega(\hat{\mathbf{k}};\hat{\ell}_1,\hat{m}_1)\,\Omega(-\hat{\mathbf{k}};\hat{\ell}_2,\hat{m}_2)\,M_{\hat{\ell}_1\hat{m}_1,\hat{\ell}_2\hat{m}_2}(\hat{\mathbf{k}}) \\ & -\left(\frac{4\pi\mu^2}{A}\right)^2\frac{NV}{2V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}}\left|\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})\right|^2(-1)^{\tilde{\ell}}\sum_{a_1,a_2}\prod_{\alpha=0}^{n}\left(\frac{\delta_{a_1,a_2}+(1-\delta_{a_1,a_2})\,C_{\ell^\alpha}}{4\pi}\right), \end{aligned} \tag{3.26}$$

where, as discussed in Sec. 2.1, the coefficients C_ℓ represent the effects of the interactions between the orbitals of a single particle (and are all less than 1 for $\ell \geq 1$), and the kernel M is given by

$$M_{\hat{\ell}_1\hat{m}_1,\hat{\ell}_2\hat{m}_2}(\hat{\mathbf{k}}) = \int_S d\hat{\mathbf{s}}\; \hat{Y}_{\hat{\ell}_1\hat{m}_1}(\hat{\mathbf{s}})\, \hat{Y}_{\hat{\ell}_2\hat{m}_2}(-\hat{\mathbf{s}})\;\; \exp(i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}). \tag{3.27}$$

We remind the reader that this linear stability analysis applies only to the higher replica sectors of the order parameter, as per the discussion in Sec. 3.2.1. The corresponding analysis applied to the one-replica sector reveals the fact, anticipated in Sec. 3.2.1, that the one-replica sector remains stable at the transition, owing to the stabilizing effect of the inter-particle interactions.

We expect the liquid state to become unstable first for long wavelengths, corresponding to $\hat{\mathbf{k}} \to \hat{\mathbf{0}}$. In this limit, $M_{\hat{\ell}_1\hat{m}_1,\hat{\ell}_2\hat{m}_2}(\hat{\mathbf{k}}) \to \delta_{\hat{\ell}_1,\hat{\ell}_2}\delta_{\hat{m}_1,\hat{m}_2}(-1)^{\tilde{\ell}+\tilde{m}}$. By examining the coefficients of the quadratic terms in Eq. (3.26), and specifically their signs, we see that for $\mu^2 < \mu_c^2 \equiv 1$ the coefficients are positive for all components of the order parameter [i.e., for all values of $(\hat{\mathbf{k}}, \hat{\ell}, \hat{m})$] and, therefore, that the free energy has a local minimum at $\Omega = 0$. Thus, for $\mu^2 \leq \mu_c^2$ the fluid state is (at least locally) thermodynamically stable. On the other hand, for $\mu^2 > \mu_c^2$, certain coefficients become negative, starting with the longest length-scale (and isotropic, corresponding to $\hat{\ell} = \hat{0}$) modes. This sign-change indicates the loss of the (linear) stability of the fluid, and the concomitant acquisition of a nonzero value of the order parameter. As usual, the linear instability of one state does not sharply specify the nature of the stable state that replaces it, although the directions of instability do provide hints. In the present setting, the residual stability of the one-replica sector suggests that the primary characteristic of the new state is macroscopic translational and rotational invariance, which is the mechanism by which the induction of energetically-costly order in the one-replica sector is avoided. Thus, it is reasonable to anticipate that the state that replaces the fluid state upon the formation of a sufficiently large density of bonds is the amorphous solid state. Furthermore, as the coefficients C_ℓ are smaller than unity for $\ell \geq 1$, and become progressively smaller with increasing ℓ, we may conclude that all anisotropic sectors remain stable, at least for bond densities in the vicinity of the amorphous solidification transition. Thus, it is reasonable to anticipate that anisotropic ordering (i.e., orientational localization) will arise only as a *response* to positional ordering, via nonlinear coupling between isotropic and anisotropic order-parameter components. Thus, as will be borne out below, we should anticipate that the form and extent of the anisotropic ordering will be computable algorithmically, as a perturbative correction to the nonperturbative result for the ordering in the isotropic sector.[2]

[2]As we are not able to compute the free energy for arbitrary values of the order parameter, we are unable to rule out the possibility, that a discontinuous phase transition occurs at a bond density smaller than μ_c^2. That the transition is continuous should be regarded as an additional assumption of ours.

CHAPTER 4

SOLUTION OF THE ORDER-PARAMETER SELF-CONSISTENT EQUATION

4.1 General Strategy

Having obtained the self-consistency equation (SCE) for the order parameter, Eq. (3.25), we now turn to the issue of solving it. We shall begin by extracting from the full SCE a transcendental self-consistency equation for the fraction of localized particles q by considering the SCE at external variables $\hat{\ell}_0 = \hat{m}_0 = \hat{0}$ and taking the limit $\hat{\mathbf{k}}_0 \to \hat{\mathbf{0}}$. By solving this equation in the vicinity of the amorphous solidification transition (i.e., for small excess crosslink densities) we will find that q tends to 0 near the transition, allowing us to expand the SCE for the order-parameter in powers of q and truncate the expansion, retaining terms of order q^2. We will then solve the SCE for individual order parameter components, starting with the only component with an unstable band, the isotropic component $\Omega(\hat{\mathbf{k}}; \hat{0}, \hat{0})$ (the unstable band being those long wavelength modes for which $\hat{\mathbf{k}}^2 < 2\epsilon$), which we shall obtain by utilizing the form of the solution, due to refs. [6, 7], and discussed in Sec. 2.2.3. The remaining (anisotropic) components are linearly stable and thus we can solve for their leading-order values perturbatively, by considering their couplings to $\Omega(\hat{\mathbf{k}}; \hat{0}, \hat{0})$. We shall obtain these anisotropic components by first solving for the leading-order contribution to the two lowest angular-momentum components, and then obtaining the solution in the general case by induction. The struc-



Figure 4.1 Component- and band-structure of the order parameter (see text for explanation).

ture of the order parameter is illustrated in Fig. 4.1, showing the different components and bands.

Throughout the entire calculation we shall only be concerned with finding the leading-order contributions to the components of Ω. This will generally imply the following: (i) truncating the expansion in powers of q (typically at second order), as near the transition we expect the fraction of localized particles to be small, (ii) ignoring the coupling of the components of the order parameter to higher angular-momentum components, as we expect $\Omega(\hat{\mathbf{k}}; \hat{\ell}, \hat{m})$ to become smaller with increasing $\hat{\ell}$, and (iii) truncating expansions in powers of $\hat{\mathbf{k}}^2$ (typically at linear order), as near the transition we can expect the particles to be weakly localized, hence we expect typical values of $\hat{\mathbf{k}}^2$ to be of order ϵ. All of these assumptions will be verified *a posteriori*. Many technical details of the calculations have been relegated to the appendices.

4.2 Fraction of Positionally Localized Particles

The first step in our solution of the order-parameter SCE is to determine the fraction of localized particles q. Following the discussion in Sec. 2.2.2, we first separate the delocalized and localized fractions in the full order parameter Ω by writing

$$\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m}) \equiv (1-q)\prod_{\alpha=0}^{n}\left(\frac{\delta_{\mathbf{k}^\alpha,\mathbf{0}}\,\delta_{\ell^\alpha,0}\,\delta_{m^\alpha,0}}{\sqrt{4\pi}}\right) + qW(\hat{\mathbf{k}};\hat{\ell},\hat{m}), \tag{4.1}$$

where $q\,W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ is the part of the order parameter describing the localized particles and is analytic at the origin, with $W(\hat{\mathbf{0}};\hat{0},\hat{0}) = 1/\sqrt{4\pi}$. The delocalized contribution cancels from the numerator and denominator of the SCE, so we may rewrite Eq. (3.25), replacing $\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ with $qW(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ in both the numerator and the denominator, obtaining

$$\Omega(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0) = \frac{\begin{array}{l}\Big\langle \frac{1}{A}\sum_{a=1}^{A} \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\,\hat{Y}^*_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_a) \\ \quad \exp\left(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}} q\,W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\right)\Big\rangle_{1,n+1}\end{array}}{\Big\langle \exp\left(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}} q\,W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\right)\Big\rangle_{1,n+1}}. \tag{4.2}$$

Following the ideas of Refs. [7, 6], to obtain a SCE for q we consider the SCE (4.2) for the order-parameter component $\Omega(\hat{\mathbf{k}}_0;\hat{0},\hat{0})$ in the limit $\hat{\mathbf{k}}_0 \to \hat{\mathbf{0}}$. We start with the SCE for $\Omega(\hat{\mathbf{k}}_0;\hat{0},\hat{0})$:

$$\begin{aligned}\Omega(\hat{\mathbf{k}}_0;\hat{0},\hat{0}) \;&=\; \mathrm{e}^{-\mu^2 q}\,\Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\left(\frac{1}{\sqrt{4\pi}}\right)^{n+1} \\ &\quad\times\exp\left(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}},\hat{\ell},\hat{m}} q\,W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\right)\Big\rangle_{1,n+1}.\end{aligned} \tag{4.3}$$

Note that the denominator of the right-hand side of Eq. (4.2) has been replaced by $\exp(\mu^2 q)$ (see App. B.2 for details). We now consider the limit $\hat{\mathbf{k}} \to \hat{\mathbf{0}}$ via a sequence for which $\tilde{\mathbf{k}} \equiv \sum_{\alpha=0}^{n}\mathbf{k}^\alpha = \mathbf{0}$. The left-hand side, as can be easily seen from Eq. (4.1), becomes $q/\sqrt{4\pi}$. To evaluate the right-hand side we follow the procedure used in App. B.2 to obtain the denominator of the right-hand side of the SCE.

We expand the exponential in a power series in q and consider the r-th order term, and pass to the replica limit $n \to 0$:

$$\Big\langle \frac{1}{r!}\left(4\pi\mu^2\right)^r q^r \sum_{\mathbf{k}_1\ell_1 m_1}\cdots\sum_{\mathbf{k}_r\ell_r m_r} W(\mathbf{k}_1;\ell_1,m_1)\cdots W(\mathbf{k}_r;\ell_r,m_r)\,\mathrm{e}^{i\mathbf{k}_0\cdot\mathbf{c}}\,\mathrm{e}^{i\mathbf{k}_1\cdot\mathbf{c}}\cdots\mathrm{e}^{i\mathbf{k}_r\cdot\mathbf{c}}$$

$$\times \frac{1}{A^r} \sum_{a_1,\ldots,a_r} \mathrm{e}^{i\mathbf{k}_1\cdot\mathbf{s}_{a_1}} \cdots \mathrm{e}^{i\mathbf{k}_r\cdot\mathbf{s}_{a_r}} Y_{\ell_1 m_1}(-\mathbf{s}_{a_1}) \cdots Y_{\ell_r m_r}(-\mathbf{s}_{a_r}) \Big\rangle_{1,1} . \tag{4.4}$$

By the MTI of $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ we know that $\tilde{\mathbf{k}}_i = \mathbf{0}$, which means that $\mathbf{k}_i = \mathbf{0}$. Also, by using the MRI of $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ we see that if $\hat{\mathbf{k}} = \hat{\mathbf{0}}$ then (B.8) can only be nonzero if $\hat{\ell} = \hat{0}$ also. Knowing that $W(\hat{0};\hat{0},\hat{0}) = 1/\sqrt{4\pi}$, for the r-th order contribution (with $r \geq 1$) we get $\frac{1}{r!}(\mu^2)^r q^r$. For $r = 0$, however, we get 0, because the limit of $\langle \exp(-i\mathbf{k}_0 \cdot \mathbf{c}) \rangle$ as $\mathbf{k}_0 \to \mathbf{0}$ is zero. By resumming the power series, we finally obtain

$$\left\langle \mathrm{e}^{i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}} \exp\left(\frac{4\pi\mu^2}{V^n} \sum_{\hat{\mathbf{k}}\hat{\ell}\hat{m}} q\, W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\, \mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}} \frac{1}{A} \sum_{a=1}^{A} \mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a} \hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_a) \right) \right\rangle_{1,n+1} =$$

$$= \sum_{r>0} \frac{1}{r!} (\mu^2)^r q^r = \exp(\mu^2 q) - 1. \tag{4.5}$$

We thus find the following self-consistency equation for the fraction of localized atoms:

$$1 - q = \exp(-\mu^2 q). \tag{4.6}$$

This self-consistency condition is precisely that obtained in the case of vulcanized macromolecules [6, 7], and earlier, in the context of random graph theory, by Erdős and Rényi (see Ref. [7]).



Figure 4.2 Graphical solution of the self-consistency equation (4.6).

We will find it convenient to exchange the control parameter μ^2 for ϵ, defined via $\mu^2 \equiv 1 + \epsilon/3$, so that ϵ vanishes as the transition is approached. The self-consistent equation for q is transcendental, but it is easy to analyze it graphically, as illustrated in Fig. 4.2. Then, for $\epsilon < 0$ we find that there is only one solution $q = 0$, corresponding to the liquid state of the system (no localized particles), and for $\epsilon > 0$ we find that for ϵ small q is small also, indicating that the fraction q of particles comprising the amorphous solid state tends to zero in the vicinity of the amorphous solidification transition. We can thus expand the exponential on the right-hand side of Eq. (4.6) obtaining the fraction q to first order in ϵ:

$$q \approx \frac{2}{3}\epsilon. \tag{4.7}$$

4.3 Perturbation Expansion for the Self-Consistency Equation

Having found the fraction q of localized particles to be small in the vicinity of the transition, we may expand the self-consistency equation for the order parameter, Eq. (4.2), in powers of q, to second order, obtaining:

$$\begin{aligned}
& q\, W(\hat{\mathbf{k}}_0; \hat{\ell}_0, \hat{m}_0) + (1-q) \prod_{\alpha=0}^{n} \left(\frac{\delta_{\mathbf{k}^\alpha,\mathbf{0}}\, \delta_{\ell^\alpha,0}\, \delta_{m^\alpha,0}}{\sqrt{4\pi}} \right) \\
\approx \quad & \mathrm{e}^{-\mu^2 q} \left\langle \frac{1}{A} \sum_{a_0=1}^{A} \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\, \hat{Y}^*_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_{a_0}) \right\rangle_{1,n+1} \\
& + \mathrm{e}^{-\mu^2 q} \left\langle \frac{1}{A} \sum_{a_0=1}^{A} \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\, \hat{Y}^*_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_{a_0}) \frac{4\pi\mu^2}{V^n} \right. \\
& \quad \times \left. \sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1} q\, W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1)\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}} \frac{1}{A} \sum_{a_1=1}^{A} \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_1}) \right\rangle_{1,n+1} \\
& + \frac{\mathrm{e}^{-\mu^2 q}}{2} \left\langle \frac{1}{A} \sum_{a_0=1}^{A} \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\, \hat{Y}^*_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_{a_0}) \frac{4\pi\mu^2}{V^n} \right. \\
& \quad \times \sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1} q\, W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1)\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}} \frac{1}{A} \sum_{a_1=1}^{A} \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_1}) \\
& \qquad \times \left. \frac{4\pi\mu^2}{V^n} \sum_{\hat{\mathbf{k}}_2,\hat{\ell}_2,\hat{m}_2} q\, W(\hat{\mathbf{k}}_2; \hat{\ell}_2, \hat{m}_2)\, \mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}} \frac{1}{A} \sum_{a_2=1}^{A} \mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_2}) \right\rangle_{1,n+1} .
\end{aligned} \tag{4.8}$$

By canceling the liquid contribution to Ω on the left-hand side with the 0-th order contribution on the right-hand side, rearranging terms and replacing $\exp(-\mu^2 q)$ with $1-q$ we arrive at the form of the SCE that we shall focus on:

$$
\begin{aligned}
& q\, W(\hat{\mathbf{k}}_0; \hat{\ell}_0, \hat{m}_0) \approx \\
& \qquad (1-q)\,\frac{4\pi\mu^2}{V^n}\, q \sum_{\hat{\mathbf{k}}_1, \hat{\ell}_1, \hat{m}_1} W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1) \\
& \qquad\qquad \times \frac{1}{A^2} \sum_{a_0, a_1 = 1}^{A} \Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\, \hat{Y}^{*}_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_{a_0})\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_1}) \Big\rangle_{1,n+1} \\
& \quad + \frac{1-q}{2} \left(\frac{4\pi\mu^2}{V^n}\right)^2 q^2 \sum_{\hat{\mathbf{k}}_1, \hat{\ell}_1, \hat{m}_1} \sum_{\hat{\mathbf{k}}_2, \hat{\ell}_2, \hat{m}_2} W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1)\, W(\hat{\mathbf{k}}_2; \hat{\ell}_2, \hat{m}_2) \\
& \quad \times \frac{1}{A^3} \sum_{a_0, a_1, a_2 = 1}^{A} \Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}_0\cdot\hat{\mathbf{c}}}\, \hat{Y}^{*}_{\hat{\ell}_0\hat{m}_0}(\hat{\mathbf{s}}_{a_0})\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_1})\, \mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2}}\, \hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_2}) \Big\rangle_{1,n+1} .
\end{aligned}
\tag{4.9}
$$

4.4 Self-Consistency Equation: Isotropic Sector

Having obtained the localized fraction q and verified the consistency of the expansion of the SCE, we now turn to the issue of solving the SCE for individual components of the order-parameter.

As discussed in Sec. 3.2.2, near to the amorphous solidification transition the only linearly unstable band of W is the long-wavelength band of the isotropic component $W(\hat{\mathbf{k}})$ (i.e., those $W(\hat{\mathbf{k}}; \hat{\ell}, \hat{m})|_{\hat{\ell}=\hat{m}=\hat{0}}$ having sufficiently small (replicated) wave vectors; specifically, $\hat{\mathbf{k}}^2 < 2\epsilon$). Thus, the basic process occurring at the transition is the acquisition of a nonzero value by the unstable components of the order parameter, which in turn perturb the stable components away from their zero values. The stable components include both the band of the isotropic component for $\hat{\mathbf{k}}^2 > 2\epsilon$ and the anisotropic components for all values of $\hat{\mathbf{k}}$. As our aim is to calculate the leading contributions to each of the components of W at small positive ϵ, we may, as a first step, proceed by computing the self-consistent value of $W(\hat{\mathbf{k}})$, neglecting the feedback on its value coming from the nonzero values that it induces in the (stable) anisotropic components [i.e., $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})|_{\hat{\ell}\neq\hat{0}}$]. Although the $\hat{\mathbf{k}}^2 > 2\epsilon$ band of the isotropic component $W(\hat{\mathbf{k}})$ is linearly stable, it is necessary to treat it self-consistently together with the unstable band, owing to the fact that they constitute a continuum (see Fig. 4.1), and therefore the stable band includes elements with an arbitrarily large "susceptibility" to perturbations caused by their couplings to the elements of the linearly unstable band [i.e., $W(\hat{\mathbf{k}})$ for $\hat{\mathbf{k}}^2 < 2\epsilon$].

We therefore consider the SCE for $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$, Eq. (4.9), for isotropic external arguments (i.e., $\hat{\ell}=\hat{m}=\hat{0}$), and ignore the effects of all anisotropic components on the right hand side. We thus arrive at the closed, nonlinear SCE for $W(\hat{\mathbf{k}}_0)$:

$$W(\hat{\mathbf{k}}_0) = \left(1 - \frac{\epsilon}{3} - \frac{\hat{\mathbf{k}}^2}{6}\right) W(\hat{\mathbf{k}}_0) + \frac{\epsilon}{3}\frac{\sqrt{4\pi}}{V^n} \sum\nolimits_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}_1) W(\hat{\mathbf{k}}_0 - \hat{\mathbf{k}}_1). \tag{4.10}$$

Precisely this equation emerges in the context of randomly crosslinked macromolecular networks, from both semi-microscopic and Landau-type approaches [6, 7]. In that context, the order parameter has (by definition) only isotropic components, in contrast with the present context. To solve Eq. (4.10) we invoke the hypothesis for $W(\hat{\mathbf{k}}_0)$ discussed in Sec. 2.2.3, viz., a parameterization in terms of the normalized probability distribution of localization lengths $p(\tau)$, along with the $\delta_{\tilde{\mathbf{k}},\mathbf{0}}$ factor, enforcing MTI of the solution:

$$W(\hat{\mathbf{k}}) = \frac{\delta_{\tilde{\mathbf{k}},\mathbf{0}}}{\sqrt{4\pi}} \int_0^\infty d\tau\, p(\tau)\, \mathrm{e}^{-\hat{\mathbf{k}}^2/2\tau}. \tag{4.11}$$

As is shown in Ref. [7], this leads to the following nonlinear integro-differential SCE for $p(\tau)$:

$$\frac{\tau^2}{2}\frac{dp}{d\tau} = \left(\frac{\epsilon}{2} - \tau\right) p(\tau) - \frac{\epsilon}{2}\int_0^\tau d\tau'\, p(\tau')\, p(\tau - \tau'), \tag{4.12}$$

i.e., precisely the equation found in Refs. [6, 7]. By making the rescalings

$$\tau \;\to\; \theta \equiv 2\tau/\epsilon, \tag{4.13}$$

$$p(\tau) \;\to\; \pi(\theta) \equiv \frac{\epsilon}{2} p(\tau), \tag{4.14}$$

as in Refs. [6, 7], we determine that the universal scaling function $\pi(\theta)$ satisfies the nonlinear integro-differential equation

$$\frac{\theta^2}{2}\frac{d\pi}{d\theta} = (1-\theta)\,\pi(\theta) - \int_0^\theta d\theta'\,\pi(\theta')\,\pi(\theta-\theta'), \tag{4.15}$$

together with the normalization condition $\int_0^\infty d\theta\,\pi(\theta) = 1$. The resulting scaled distribution $\pi(\theta)$ can be obtained numerically, and the result is given in Refs. [6, 7]. (The prediction for this universal scaling function is compared with results from numerical simulations in Ref. [9].) Thus we have obtained the isotropic component $W(\hat{\mathbf{k}})$ of the order parameter $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ in the vicinity of the transition. As we have discussed in Sec. 2.2.1, we are thus in possession of statistical information concerning the spatial localization of particles, regardless of the angular localization of the orbitals.

4.5 Self-Consistency Equation: Anisotropic Sectors

We now turn to the task of calculating the leading-order contributions to the *anisotropic* components of $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ [i.e., $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})|_{\hat{\ell}\neq\hat{0}}$]. We remind the reader that the anisotropic components are all linearly stable near the transition, and not merely infinitesimally so (i.e., linear stability analysis indicates that none of these anisotropic components even become marginally stable at the transition). Note the contrast with the stable band of the isotropic component [$W(\hat{\mathbf{k}})$ for $\hat{\mathbf{k}}^2 > 2\epsilon$], which, though stable, do include marginally stable components (i.e., components of arbitrarily small "mass"). Unlike the stable band of the isotropic component the (also stable) anisotropic components are separated by a "gap" from the unstable components, owing to the discreteness of the external variable $\hat{\ell}$, the components of which take on integer values only, in contrast with the components of $\hat{\mathbf{k}}$, which are continuous (in the thermodynamic limit). It is this "gap" that allows us to obtain the stable anisotropic components by means of perturbation theory, which we could not use to solve for the stable band of the isotropic component (see Fig. 4.1).

4.5.1 Anisotropic sector: angular momentum 1 in one replica channel

Rather than begin with generalities, we first consider the lowest angular momentum sector $\{W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\}_{\hat{\ell}^2=2}$ (i.e., the collection of order-parameter components $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ such that $\hat{\ell}^2 \equiv \sum_\alpha \ell^\alpha(\ell^\alpha+1) = 2$). In this case $\hat{\ell}$ is some permutation of the form $(0,1,0,0,\ldots,0)$. We therefore consider the SCE for $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$, i.e., Eq. (4.9) for the anisotropic external argument

$$\begin{array}{ll} \text{replica} & \begin{matrix} 0 & 1 & \ldots & \alpha_1 & \alpha_1+1 & \ldots & n \end{matrix} \\ \begin{matrix} \hat{\ell} \\ \hat{m} \end{matrix} & \begin{pmatrix} 0, & 0, & \ldots, & 1, & 0, & \ldots, & 0 \\ 0, & 0, & \ldots, & m_1, & 0, & \ldots, & 0 \end{pmatrix}, \end{array} \tag{4.16}$$

and arbitrary $\hat{\mathbf{k}}$, which, as we establish in App. B.3, reads

$$W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) = \mathcal{C}^{(0)}\left(-W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) + \frac{i}{\sqrt{3}}W(\hat{\mathbf{k}}_1)\,k^{\alpha_1\,*}_{m_1} - q\frac{\sqrt{4\pi}}{V^n}\sum\nolimits_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\,W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_1)\right). \tag{4.17}$$

The symbol $k^{\alpha\,*}_m$ denotes the complex conjugate of the m-th spherical tensor component of the vector $\mathbf{k}^\alpha$ spherical component of the vector $\mathbf{k}^\alpha$ and is defined via

$$k^*_m \equiv \sqrt{\frac{4\pi}{3}}\,k\,Y^*_{1m}(\mathbf{k}/k). \tag{4.18}$$

The parameter $\mathcal{C}^{(0)}$ encodes physical information arising from orbital-orbital correlations of a single particle and is defined in App. A.3. Specifically, $\mathcal{C}^{(0)}$ depends on the $\ell=1$ value of the free-particle two-orbital orientation correlator, renormalized by the one-replica sector contributions $\langle Y^*_{\ell m}(\mathbf{s}_a)\,Y_{\ell' m'}(\mathbf{s}_{a'})\rangle_{1,1}$. The permutation symmetry among the A orbitals and rotational invariance of the joint probability distribution of their orientations restrict this correlator to have the form

$$\Big\langle Y^{*}_{\ell m}(\mathbf{s}_a)\, Y_{\ell' m'}(\mathbf{s}_{a'})\Big\rangle_{1,1} = \frac{1}{4\pi}\delta_{\ell,\ell'}\,\delta_{m,m'}\Big(\delta_{a,a'} + (1-\delta_{a,a'})\, C_\ell\Big), \tag{4.19}$$

characterized by the parameters $\{C_\ell\}_{\ell=1}^{\infty}$ (with $C_0 = 1$, by normalization), introduced in Sec. 2.1. As for the issue of what terms have been omitted in arriving at Eq. (4.17), we are concerned only with the leading-order values of the components of W, and therefore, here and elsewhere, shall omit terms that do not alter leading-order values. In particular, in arriving at Eq. (4.17) from Eq. (4.9) we have neglected all components of W having $\hat{\ell}^2 \geq 2$. Such terms are sufficiently small that feedback from them would not alter the leading-order value of $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$. We shall verify the internal consistency of this assumption below. In addition, we have kept only terms carrying sufficiently few powers of components of $\hat{\mathbf{k}}$. As the characteristic value of $\hat{\mathbf{k}}^2$ is of order ϵ, higher powers render terms subdominant. The steps leading from Eq. (4.9) to Eq. (4.17) are explained in detail in App. B.3.

To solve Eq. (4.17) we rewrite it in the form of a (Type II Inhomogeneous) integral equation by moving the first term on the right hand side to the left, regarding the second term as a known inhomogeneity, and the third term as a perturbation (see App. B.3 for details of this calculation). We then solve this equation iteratively, thus obtaining

$$W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) = \frac{i}{\sqrt{3}}\mathcal{C}^{(1)}\, W(\hat{\mathbf{k}})\, k^{\alpha_1\,*}_{m_1}, \tag{4.20}$$

where the parameter $\mathcal{C}^{(1)}$ depends on A and C_1 (see App. A.3). In fact, for this particular component of W our procedure merely amounts to truncating the Born series after the *zeroth* order (i.e., effectively ignoring the perturbation altogether), and solving the resulting algebraic equation. However, for certain other components it turns out to be necessary to retain the first-order term, for reasons that we shall explain below.

As we have discussed in Sec. 2.2.1, the result that we have just obtained about the value of the order-parameter component $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$ yields statistical information concerning the variations, across the system, of the strength of the correlations between the thermal fluctuations of the positions of the localized particles and the thermal fluctuations of the orientations of their orbitals. We will discuss this information in more detail in Sec. 5.3

4.5.2 Anisotropic sector: angular momentum 1 in two replica channels

Having obtained the leading-order contributions to the order-parameter components $W(\hat{\mathbf{k}})$ and $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$ [i.e., the isotropic (largest) and anisotropic (next largest) components], we now address the component of W corresponding to

$$\begin{array}{ll} \text{replica} & \begin{array}{ccccccccc} 0 & 1 & \ldots & \alpha_1 & \alpha_1+1 & \ldots, & \alpha_2 & \alpha_2+1 & \ldots \quad n \end{array} \\ \begin{array}{c} \hat{\ell} \\ \hat{m} \end{array} & \begin{pmatrix} 0, & 0, & \ldots, & 1, & 0, & \ldots, & 1, & 0, & \ldots, & 0 \\ 0, & 0, & \ldots, & m_1, & 0, & \ldots, & m_2 & 0, & \ldots, & 0 \end{pmatrix}, \end{array} \tag{4.21}$$

which we denote by $W^{\alpha_1\,\alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$. The motivation for examining this component is that, in contrast to the components $W(\hat{\mathbf{k}})$ and $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$, the limit $\hat{\mathbf{k}} \to \hat{\mathbf{0}}$ of this component provides information purely about the orientational localization of the orbitals, independent of the positional localization properties, as we shall discuss in more detail in Sec. 5.3.

As shown in App. B.4, the retention of all terms that give rise to leading-order contributions to $W^{\alpha_1\,\alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$ leads to the following SCE for this component:

$$\begin{aligned} W^{\alpha_1\,\alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}) \quad = \quad & \mathcal{C}^{(2)} W^{\alpha_1\,\alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}) - \frac{1}{3}\mathcal{C}^{(3)} k^{\alpha_1\,*}_{m_1} k^{\alpha_2\,*}_{m_2} W(\hat{\mathbf{k}}) \\ & + q\mathcal{C}^{(2)} \frac{\sqrt{4\pi}}{2V^n} \sum\nolimits_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}} - \hat{\mathbf{k}}_1)\, W^{\alpha_1\,\alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}_1) \\ & + q\mathcal{C}^{(2)} \frac{\sqrt{4\pi}}{V^n} \sum\nolimits_{\hat{\mathbf{k}}_1} W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}} - \hat{\mathbf{k}}_1)\, W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}_1), \end{aligned} \tag{4.22}$$

where the parameters $\mathcal{C}^{(2)}$ and $\mathcal{C}^{(3)}$ depend on A and C_1 (see App. A.3). On the basis of the transformation properties of this equation under common rotations of the replicas (and bearing in mind the coupling between positional and orientational degrees of freedom), we propose that the solution has the form

$$W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}}) = (-1)^{m_1}\,\delta_{m_1+m_2,0}\,w^{(1)}(\hat{\mathbf{k}}^2) + k^{\alpha_1\,*}_{m_1}\,k^{\alpha_2\,*}_{m_2}\,w^{(2)}(\hat{\mathbf{k}}^2), \tag{4.23}$$

parametrized in terms of the two as-yet unknown functions $w^{(1)}$ and $w^{(2)}$, which each depend only on $\hat{\mathbf{k}}^2$. By inserting this proposed form into Eq. (4.22), contracting (on the indices m_1 and m_2), first with $(-1)^{m_1}\,\delta_{m_1+m_2,0}$ and then with $k^{\alpha_1\,*}_{m_1}\,k^{\alpha_2\,*}_{m_2}$, and considering the limit $\mathbf{k}^{\alpha^1} = \mathbf{k}^{\alpha^2} \to \mathbf{0}$ (with $\hat{\mathbf{k}}^2$ fixed and arbitrary), and retaining only terms that contribute to the leading-order value of $W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}})$, we arrive at the pair of coupled (Type II inhomogeneous) integral equations

$$\mathcal{C}^{(4)}\,w^{(2)}(\hat{\mathbf{k}}^2) = -\frac{1}{3}\frac{\mathcal{C}^{(3)}}{\mathcal{C}^{(2)}}\,W(\hat{\mathbf{k}}), \tag{4.24}$$

$$\begin{aligned}\mathcal{C}^{(4)}\,w^{(1)}(\hat{\mathbf{k}}^2) = {}& \frac{q\sqrt{4\pi}}{V^n}\sum\nolimits_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\,w^{(1)}(\hat{\mathbf{k}}_1^2) \\ &+q\,\frac{\sqrt{4\pi}}{V^n}\Big\{\sum\nolimits_{\hat{\mathbf{k}}_1} W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\,W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}_1)\Big\}_\delta \\ &+q\,\frac{\sqrt{4\pi}}{V^n}\Big\{\sum\nolimits_{\hat{\mathbf{k}}_1} k^{\alpha_1\,*}_{1\,m_1}\,k^{\alpha_2\,*}_{1\,m_2}\,w^{(2)}(\hat{\mathbf{k}}_1^2)\,W(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\Big\}_\delta,\end{aligned} \tag{4.25}$$

where the parameter $\mathcal{C}^{(4)}$ depends on A and C_1 (see App. A.3). The symbol $\{\cdots\}_\delta$ denotes the result of extracting from the quantity inside the braces the coefficient of the term proportional to the isotropic rank-2 spherical tensor $(-1)^{m_1}\delta_{m_1+m_2,0}$. [To extract this part, we take the limit $\mathbf{k}^{\alpha^1} = \mathbf{k}^{\alpha^2} \to \mathbf{0}$ with $\hat{\mathbf{k}}^2$ fixed and arbitrary, and contract with $(-1)^{m_1}\delta_{m_1+m_2,0}/3$.] To find the leading contributions to $w^{(1)}$ and $w^{(2)}$ we first read off the value of the latter from Eq. (4.24). We then use this result to eliminate $w^{(2)}$ from Eq. (4.25), observing that we can omit the first term on the right hand side of Eq. (4.25), and perform the remaining summations to arrive at the results

$$w^{(2)}(\hat{\mathbf{k}}^2) = -\frac{1}{3}\,\mathcal{C}^{(5)}\frac{1}{\sqrt{4\pi}}\int_0^\infty d\theta\,\pi(\theta)\,\mathrm{e}^{-\hat{\mathbf{k}}^2/\epsilon\theta}, \tag{4.26}$$

$$w^{(1)}(\hat{\mathbf{k}}^2) = \frac{\mathcal{C}^{(6)}}{\sqrt{4\pi}}\frac{\epsilon^2}{4}\int_0^\infty d\theta\,\kappa(\theta)\,\mathrm{e}^{-\hat{\mathbf{k}}^2/\epsilon\theta}, \tag{4.27}$$

$$\begin{aligned}\theta\kappa(\theta) \;\equiv\; & \int_0^\infty d\theta_1\,\pi(\theta_1)\,d\theta_2\,\pi(\theta_2)\,\theta_1\theta_2\delta(\theta-(\theta_1+\theta_2)) \\ & = \Big((\theta\,\pi(\theta)) * (\theta\,\pi(\theta))\Big)(\theta),\end{aligned} \tag{4.28}$$

where the symbol $*$ represents Laplace convolution. Note that, as can be anticipated from our perturbative approach to obtaining the anisotropic components, the results for $w^{(1)}$ and $w^{(2)}$ are constructed algorithmically from the universal scaling function $\pi(\theta)$.

4.5.3 Self-consistency equation: general case

Having obtained the isotropic component of W, as well as the two lowest angular momentum anisotropic components, we now address the task of establishing the general form of W, along with an algorithm for obtaining the leading-order contributions to W for arbitrary values of its arguments. We begin by proposing the following structure for the general form of the leading-order contribution to $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$:

$$W(\hat{\mathbf{k}};\hat{\ell},\hat{m}) \approx \mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})\,W(\hat{\mathbf{k}}) + \epsilon^{1+\frac{1}{2}\tilde{\ell}}\,\mathcal{T}_{\hat{\ell},\hat{m}}\int_0^\infty d\theta\,\pi_{\hat{\ell},\hat{m}}(\theta)\,\mathrm{e}^{-\hat{\mathbf{k}}^2/\epsilon\theta}. \tag{4.29}$$

Here $\mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})$ is a certain homogeneous polynomial in $k_m^{(\ell)}$ in which all terms are of order $\tilde{\ell}$ in k. (We remind the reader that $k_m^{(\ell)}$ stands for $\sqrt{(2\ell+1)/4\pi}\,k^\ell\,Y_{lm}\,(\mathbf{k}/k)$, and is thus of order ℓ in k.) In addition, $\mathcal{T}_{\hat{\ell},\hat{m}}$ is a certain rotationally-invariant tensor depending only on $\hat{\ell}$ and $\hat{m}$, and $\pi_{\hat{\ell},\hat{m}}(\theta)$ is a distribution. All the unknown ingredients [$\mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})$, $\mathcal{T}_{\hat{\ell},\hat{m}}$, and $\pi_{\hat{\ell},\hat{m}}(\theta)$] will be obtained below.

To illustrate these notions with a concrete example we note that $W^{\alpha_1\;\alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}})$, constructed in Sec. 4.5.2, has such a form, with

$$\mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})|_{\hat{\ell}=(0,\dots,0,1,1,0,\dots,0)} \;=\; -\frac{1}{3}\,\mathcal{C}^{(5)}\,k_{m_1}^{\alpha_1\,*}\,k_{m_2}^{\alpha_2\,*}, \tag{4.30}$$

$$\mathcal{T}_{\hat{\ell},\hat{m}}|_{\hat{\ell}=(0,\dots,0,1,1,0,\dots,0)} \;=\; (-1)^{m_1}\delta_{m_1+m_2,0}, \tag{4.31}$$

$$\pi_{\hat{\ell},\hat{m}}(\theta)|_{\hat{\ell}=(0,\dots,0,1,1,0,\dots,0)} \;=\; \frac{\mathcal{C}^{(6)}}{4\sqrt{4\pi}}\,\kappa(\theta), \tag{4.32}$$

where $\hat{\ell} = (0, \ldots, 0, 1, 1, 0, \ldots, 0)$ indicates that $\ell^{\alpha_1} = \ell^{\alpha_2} = 1$, with $\ell^{\alpha} = 0$ in all other replicas. Note that $\mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})|_{\hat{\ell}=(0,\ldots,0,1,1,0,\ldots,0)}$ is of order $\tilde{\ell}(=2)$ in components of $\hat{\mathbf{k}}$.

To show that the leading-order contribution to the general component $W(\hat{\mathbf{k}}; \hat{\ell}, \hat{m})$ in the vicinity of the amorphous solidification transition does indeed have the form (4.29) for all values of $\hat{\ell}$, $\hat{m}$, and $\hat{\mathbf{k}}$, we proceed by full mathematical induction on the multi-index $\hat{\ell}$.[1] We note that $W(\hat{\mathbf{k}})$ has this form with $\mathcal{P}_{\hat{0},\hat{0}}(\hat{\mathbf{k}}) = 1$ and $\pi_{\hat{0},\hat{0}}(\theta) = 0$, thus establishing the *base* of induction. To establish the *step* of induction we assume that $W(\hat{\mathbf{k}}; \hat{\ell}, \hat{m})$ has the form (4.29) for all values $\hat{\ell} < \hat{\ell}_0$ (which means that $\ell^{\alpha} \leq \ell_0^{\alpha}$ for all α, and $\ell^{\alpha} < \ell_0^{\alpha}$ for at least one α). We then examine the SCE for $W(\hat{\mathbf{k}}_0; \hat{\ell}_0, \hat{m}_0)$:

$$\begin{aligned}
W(\hat{\mathbf{k}}_0; \hat{\ell}_0, \hat{m}_0) \quad = \quad & (1-q)\frac{4\pi\mu^2}{V^n} \sum_{\hat{\mathbf{k}}_1, \hat{\ell}_1, \hat{m}_1} W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1) \\
& \times \frac{1}{A^2} \sum_{a_0, a_1 = 1}^{A} \left\langle \mathrm{e}^{-i\hat{\mathbf{k}}_0 \cdot \hat{\mathbf{c}}}\, \hat{Y}^*_{\hat{\ell}_0 \hat{m}_0}(\hat{\mathbf{s}}_{a_0})\, \mathrm{e}^{i\hat{\mathbf{k}}_1 \cdot \hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_1 \cdot \hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}_1 \hat{m}_1}(-\hat{\mathbf{s}}_{a_1}) \right\rangle_{1,n+1} \\
& + \frac{1}{2}\left(\frac{4\pi\mu^2}{V^n}\right)^2 q \sum_{\hat{\mathbf{k}}_1, \hat{\ell}_1, \hat{m}_1} \sum_{\hat{\mathbf{k}}_2, \hat{\ell}_2, \hat{m}_2} W(\hat{\mathbf{k}}_1; \hat{\ell}_1, \hat{m}_1)\, W(\hat{\mathbf{k}}_2; \hat{\ell}_2, \hat{m}_2) \\
\times \frac{1}{A^3} \sum_{a_0, a_1, a_2 = 1}^{A} & \left\langle \mathrm{e}^{-i\hat{\mathbf{k}}_0 \cdot \hat{\mathbf{c}}}\, \hat{Y}^*_{\hat{\ell}_0 \hat{m}_0}(\hat{\mathbf{s}}_{a_0})\, \mathrm{e}^{i\hat{\mathbf{k}}_1 \cdot \hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_1 \cdot \hat{\mathbf{s}}_{a_1}}\, \hat{Y}_{\hat{\ell}_1 \hat{m}_1}(-\hat{\mathbf{s}}_{a_1})\, \mathrm{e}^{i\hat{\mathbf{k}}_2 \cdot \hat{\mathbf{c}}}\, \mathrm{e}^{i\hat{\mathbf{k}}_2 \cdot \hat{\mathbf{s}}_{a_2}}\, \hat{Y}_{\hat{\ell}_2 \hat{m}_2}(-\hat{\mathbf{s}}_{a_2}) \right\rangle_{1,n+1}.
\end{aligned} \tag{4.33}$$

As we are are only concerned with leading-order contributions to W, we truncate the $\hat{\ell}$ sums in Eq. (4.33) so as to include only terms with $\hat{\ell} \leq \hat{\ell}_0$. We now examine the contributions to $W(\hat{\mathbf{k}}_0, \hat{\ell}_0, \hat{m}_0)$ coming from linear couplings to lower-angular momentum components of W [i.e., the terms in the right-hand side of Eq. (4.33) that are linear in W]. Consider the coupling to $W(\hat{\mathbf{k}}, \hat{\ell}, \hat{m})$. Owing to the translational invariance of the correlator, by performing the $\hat{\mathbf{c}}$ average in Eq. (4.33) we establish that $\hat{\mathbf{k}} = \hat{\mathbf{k}}_0$. The

[1] We remind the reader that *full mathematical induction* is the version of the technique of induction in which the validity of a statement for all integers n less than some integer N is required to establish the validity of the statement for N. Perhaps more familiar is *mathematical induction*, in which the validity of a statement for the integer $N-1$ is all that is required to establish the validity of the statement for N. For a discussion, see, e.g., *Encyclopedic Dictionary of Mathematics*, edited by Kiyosi Itô (MIT Press, Cambridge, MA, 1993).

remaining correlator factorizes on the replica index, becoming

$$\prod_{\alpha=0}^{n} \left\langle Y^*_{\ell_0^\alpha m_0^\alpha}(\mathbf{s}^\alpha_{a_0})\, Y_{\ell^\alpha m^\alpha}(-\mathbf{s}^\alpha_{a_1})\, \mathrm{e}^{i\mathbf{k}_0^\alpha\cdot\hat{\mathbf{s}}^\alpha_{a_1}} \right\rangle_{1,n+1}. \tag{4.34}$$

By introducing the Rayleigh-expansion for the factor $\exp(i\mathbf{k}_0^\alpha \cdot \hat{\mathbf{s}}^\alpha_{a_1})$ (see App. A.1 for details) we see that this correlator is nonzero only for the terms of order ℓ'^α in the Rayleigh expansion for which the angular momenta ℓ'^α, ℓ_0^α, and ℓ^α can sum to angular momentum 0. As we are only interested in the leading-order contributions to W, and the ℓ'^α term in the Rayleigh expansion is of order $(k_0^\alpha)^{\ell'^\alpha}$, we need only keep the lowest angular-momentum term (i.e., $\ell'^\alpha = \ell_0^\alpha - \ell^\alpha$). Thus, from each replica we shall pick up the factors $(k_0^\alpha)^{(\ell_0^\alpha-\ell^\alpha)}_{m_0^\alpha-m^\alpha}$, provided, of course, that the angular-momentum inequalities $|m_0^\alpha - m^\alpha| \le \ell_0^\alpha - \ell^\alpha$ are met. From all replicas together, these factors will give a factor depending on the $\{k_m^{(\ell)}\}$ that will be of order $\tilde{\ell}_0 - \tilde{\ell}$ in k. To leading order, the term that corresponds to the coupling of $W(\hat{\mathbf{k}}_0, \hat{\ell}_0, \hat{m}_0)$ to $W(\hat{\mathbf{k}}, \hat{\ell}, \hat{m})$ will thus become,

$$\left(\prod_{\alpha=0}^{n} (k_0^\alpha)^{(\ell_0^\alpha-\ell^\alpha)}_{m_0^\alpha-m^\alpha}\, C^\alpha_{\hat{\ell}_0,\hat{m}_0;\hat{\ell},\hat{m}}\right) \mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}}_0)\, W(\hat{\mathbf{k}}_0), \tag{4.35}$$

where the $C^\alpha_{\hat{\ell}_0,\hat{m}_0;\hat{\ell},\hat{m}}$ are constants, for which we cannot in general provide a closed-form result, but which we can, however, compute, should we decide to construct some component of the order parameter explicitly, as we have, e.g., done for $W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}$.

As $\prod_{\alpha=0}^{n} (k_0^\alpha)^{(\ell_0^\alpha-\ell^\alpha)}_{m_0^\alpha-m^\alpha}$ is of order $\tilde{\ell}_0 - \tilde{\ell}$ in k_0, and as $\mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}}_0)$ is, according to the inductive assumption, of order $\tilde{\ell}$, we see that this contribution is of order $\tilde{\ell}_0$ in k_0. Taking the term corresponding to $\hat{\ell} = \hat{\ell}_0, \hat{m} = \hat{m}_0$ over to the left-hand side, adding all remaining terms, and making the definition

$$\mathcal{P}_{\hat{\ell}_0,\hat{m}_0}(\hat{\mathbf{k}}_0) \equiv \sum_{\hat{\ell}<\hat{\ell}_0}\sum_{\hat{m}} \left(\prod_{\alpha=0}^{n} C^\alpha_{\hat{\ell}_0,\hat{m}_0;\hat{\ell},\hat{m}}\, (k_0^\alpha)^{(\ell_0^\alpha-\ell^\alpha)}_{m_0^\alpha-m^\alpha}\right) \mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}}_0), \tag{4.36}$$

we see that, to leading order in k_0, the linear contribution to $W(\hat{\mathbf{k}}_0; \hat{\ell}_0, \hat{m}_0)$ is indeed of the form (4.29), with $\mathcal{P}_{\hat{\ell}_0,\hat{m}_0}(\hat{\mathbf{k}}_0)$ being of the correct order in k_0. As, due to the fact that q is small near the transition, the linear contribution is of lower order in ϵ than the quadratic terms for values of $\hat{\mathbf{k}}^2$ of order ϵ, we have thus also established a recursive algorithm for determining $\mathcal{P}_{\hat{\ell}_0,\hat{m}_0}(\hat{\mathbf{k}}_0)$. Illustrations of its use can be found in Apps. B.3 and B.4.

We now examine the *quadratic* contribution to $W(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0)$ in Eq. (4.29). This term is only the dominant one for $\hat{\mathbf{k}}_0^2 \ll \epsilon$ and, hence, we need only obtain it in the limit $\hat{\mathbf{k}}_0^2 \to 0$, which is equivalent to extracting from it the leading-order contribution to the part proportional to the ($\mathbf{k}$-independent) rotationally-invariant tensor $\mathcal{T}_{\hat{\ell}_0,\hat{m}_0}$. As we are interested only in the leading-order behavior of W, in the summations over $\hat{\ell}$ in the quadratic term of Eq. (4.33) we need only include the linear contributions to $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ [i.e., for the purposes of computing the quadratic term of $W(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0)$ we can set $W(\hat{\mathbf{k}};\hat{\ell},\hat{m}) = \mathcal{P}_{\hat{\ell},\hat{m}}(\hat{\mathbf{k}})\,W(\hat{\mathbf{k}})$ for $\hat{\ell} \leq \hat{\ell}_0$].

Having examined the intra-sector quadratic coupling of $W(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0)$ we now turn to the inter-sector quadratic coupling [i.e., the quadratic coupling of $W(\hat{\mathbf{k}}_0;\hat{\ell}_0,\hat{m}_0)$ to lower angular-momentum components]. In each replica α we have four sources of angular momentum: two (ℓ_1^α and ℓ_2^α) coming from the two components of W [i.e., $W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1)$ and $W(\hat{\mathbf{k}}_2;\hat{\ell}_2,\hat{m}_2)$]; and two (${\ell'}_1^\alpha$ and ${\ell'}_2^\alpha$), one coming from each of the Rayleigh expansions of the "shift" factors $\exp(i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1})$ and $\exp(i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2})$. As we are only interested in the leading-order behavior of W, we need only consider the case when $\ell_1^\alpha+\ell_2^\alpha+{\ell'}_1^\alpha+{\ell'}_2^\alpha=\ell_0^\alpha$. Each source of angular momentum ℓ brings with it a factor of k^ℓ. Hence, by multiplying all factors from all replicas together and assembling all terms in the summations we obtain

$$qV^{-n}\Big\{ \textstyle\sum_{\hat{\mathbf{k}}_1,\hat{\mathbf{k}}_2} \mathcal{F}(\hat{\mathbf{k}}_1,\hat{\mathbf{k}}_2)\,W(\hat{\mathbf{k}}_1)\,W(\hat{\mathbf{k}}_2)\,\delta_{\hat{\mathbf{k}}_1+\hat{\mathbf{k}}_2,\hat{\mathbf{k}}_0}\,\delta_{\tilde{\mathbf{k}}_1,\mathbf{0}}\,\delta_{\tilde{\mathbf{k}}_2,\mathbf{0}}\Big\}_{\mathcal{T}}, \tag{4.37}$$

where the operation $\{\cdots\}_{\mathcal{T}}$ denotes the extraction from $\cdots$ of the part proportional to $\mathcal{T}_{\hat{\ell}_0,\hat{m}_0}$, and where $\mathcal{F}$ is a polynomial function of k_1 and k_2 in which all terms are of order

$\tilde{\ell}_0$. Provided that $\hat{\ell}_0$ and $\hat{m}_0$ satisfy conditions for macroscopic rotational invariance (note, in particular, that MRI requires $\tilde{\ell}_0$ to be even and, hence, that the quadratic contribution vanishes for $\tilde{\ell}_0$ odd), we can perform the summations, indeed obtaining the claimed structure for the second-order term in Eq. (4.29). Thus, we have established a recursive procedure for obtaining $\pi_{\hat{\ell}_0,\hat{m}_0}(\theta)$. Keeping in mind that typical values of $\hat{\mathbf{k}}_0^2$ are of order ϵ, that $q = 2/3\epsilon$, and that $W(\hat{\mathbf{k}})$ is of order unity, we verify the scaling of the quadratic term to be $\epsilon^{(\tilde{\ell}_0/2)+1}$, thus completing the *step* of induction, viz. the second and final element of our proof.

To conclude our discussion of the solution of the order-parameter SCE we note that all the assumptions that we have made in Sec. 4.1 regarding the scaling (with ϵ) of various quantities are verified, *a posteriori*, by the solution that we have obtained, thus establishing the self-consistency of these assumptions.

CHAPTER 5

PHYSICAL INFORMATION ENCODED IN THE ORDER PARAMETER

5.1 Introduction

We have constructed the solution of the order-parameter self-consistency equation in the vicinity of the amorphous solidification transition, Eq. (4.29), and have obtained explicit solutions for the two lowest angular-momentum components of the order parameter, Eqs. (4.20,4.26,4.27). We are thus in possession of a range of statistical information about the amorphous solid state, this information being encoded in the order parameter, as discussed in Sec. 2.2.1. In this section we (i) explicitly extract some of this information from the two lowest angular-momentum components of the order parameter, (ii) provide a strategy for obtaining other statistical information about the system from higher angular-momentum components, and (iii) discuss the scaling of the order parameter with ϵ near the transition, as well as the implications of this scaling.

Our statistical diagnosis of the structure of the amorphous solid state in the vicinity of the amorphous solidification transition is made in terms of the moments of the joint distribution function P that collects together the localization characteristics of all the particles in the sample and their orbitals, averaged over realizations of the disorder (see Sec. 2.2.1). As we shall see, we are unable to construct the entire distribution function, or even to construct a closed-form expression for arbitrary moments. However, most of the useful information about the system can be obtained from low moments of the distribution, resulting from the two lowest angular-momentum components of the order parameter, which we have obtained explicitly. As for the information encoded in the higher angular-momentum components of the order parameter, we do not extract it explicitly. We do, however, describe the kind of information that could be obtained from them, as well as provide the general procedure for doing so.

5.2 Encoded Information: Isotropic Sector



Figure 5.1 The universal distribution of localization lengths.

We begin by discussing the statistical information encoded in the isotropic component of the order parameter $W(\hat{\mathbf{k}}^2)$. In Sec. 4.4 we have obtained this component in the vicinity of the amorphous solidification transition and, consequently, have obtained the reduced distribution of (inverse square) localization lengths $p(\tau)$ associated with localized particles. The fact that $p(\tau)$ takes on a scaling form, and that the scaling function $\pi(\theta)$ (see Fig. 5.1 for the numerical solution obtained by Castillo and collaborators in Ref. [7]) has a well defined peak (with location and width both of order unity), allows us to establish that (as $\epsilon \to 0$) τ scales as ϵ and, accordingly, ξ scales as $\epsilon^{-1/2}$. For example, any reasonable choice for a characteristic value of ξ [say $\int_0^\infty d\tau\, p(\tau)\, \tau^{-1/2}$] scales as $\epsilon^{-1/2}$.

In the present context, while the emergent distribution $p(\tau)$ is found to have striking scaling properties, there is the suspicion that changes in the details of the model will lead to changes at least in the details of the scaling function $\pi(\theta)$ or, perhaps, in the scaling property itself. However, it has been found in the context of vulcanized macromolecular matter that the scaling property, as well as the precise form of the scaling function, are robust, universal features of the mean-field theory [9], verified by independent computer simulations [8]. Moreover, this universality has been found to have its origins in the symmetries of the appropriate Landau free energy and the divergence (at the transition) of the characteristic localization length.

Being in possession of the entire distribution of localization lengths provides us with a surprisingly rich characterization of the positional aspects of the amorphous solid state. It is striking that the distribution is universal, not only across the macromolecular systems where it was first found, but also in the present setting of vitreous media. Although we have obtained the distribution via analysis of a specific semi-microscopic model of vitreous media, we anticipate that, here too, the result will have a broader domain of applicability. Moreover, given the emerging picture of orientational order as order *slaved* to the underlying positional order, it is not surprising—and indeed we shall demonstrate this point below—that all other statistical descriptors of the amorphous solid state are also constructed from the universal function $\pi(\theta)$.

5.3 Encoded Information: Low Angular-Momentum Anisotropic Sectors

5.3.1 Angular localization

We now discuss some of the specific physical information that can be obtained by examining our explicit solutions for the two lowest angular-momentum components of the order parameter, which we have obtained in Secs. 4.5.1 and 4.5.2. The first piece of information concerns the angular localization of the orbitals, without regard to the positional localization of the particles. As we recall from Sec. 2.2.1, such information is accessed via the order parameter for $\hat{\mathbf{k}} = \hat{\mathbf{0}}$, and is described by the distribution of the collection of characteristics $\{\Sigma_{\ell m}\}$. We note that $W^{\alpha_1}_{1m_1}(\hat{\mathbf{0}})$ is zero (this is a consequence of MRI, as discussed in sec. 4.5.3). Thus the lowest angular-momentum order-parameter component that provides access to this information is $W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}})$, the solution for which is given by Eq. (4.23). Evaluating this order-parameter component at $\hat{\mathbf{k}} = \hat{\mathbf{0}}$ gives

$$q\, W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{0}}) = (-1)^{m_1}\delta_{m_1+m_2,0}\frac{\mathcal{C}^{(6)}}{\sqrt{4\pi}}\frac{\epsilon^3}{6}\int_0^\infty d\theta\, \kappa(\theta), \tag{5.1}$$

where $\kappa(\theta)$ is given in Eq. 4.28. Now, recalling the interpretation of the order parameter developed in Sec. 2.2.1, we arrive at

$$\begin{aligned} q \int d\tau\, d\{\Sigma\}\, \mathcal{D}\{\Gamma\}\, P(\tau, \{\Sigma\}, \{\Gamma\})\, \Sigma_{1,m_1}\, \Sigma_{1,m_2} \\ = \left[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\left\langle Y^*_{1m_1}(\mathbf{s}_{j,a})\right\rangle \left\langle Y^*_{1m_2}(\mathbf{s}_{j,a})\right\rangle\right] \\ = (-1)^{m_1}\delta_{m_1+m_2,0}\frac{\mathcal{C}^{(6)}}{\sqrt{4\pi}}\frac{\epsilon^3}{6}\int_0^\infty d\theta\, \kappa(\theta). \end{aligned} \tag{5.2}$$

Notice that this characteristic of the angular localization of the orbitals is essentially the order parameter traditionally used to describe the directional localization of magnetic moments in the spin-glass state. In fact, if we recall the spherical-tensor decomposition of the scalar product of two unit vectors, $\mathbf{s}_1 \cdot \mathbf{s}_2 = \sum_{m=-1}^{m=+1}(-1)^m Y_{1m}(\mathbf{s}_1) Y_{1-m}(\mathbf{s}_2)$

then, by appropriately contracting Eq. (5.2) over m_1 and m_2, we obtain the familiar characterization of directional localization:

$$\left[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\langle \mathbf{s}_{j,a}\rangle\cdot\langle \mathbf{s}_{j,a}\rangle\right] = \frac{3\,\mathcal{C}^{(6)}}{\sqrt{4\pi}}\frac{\epsilon^3}{6}\int_0^\infty d\theta\,\kappa(\theta). \tag{5.3}$$

The interpretation of the scaling of this quantity with ϵ will be discussed in Sec. 5.4.

5.3.2 Angle-position fluctuation correlations

Further specific physical information concerns the degree to which the thermal fluctuations in the orbital orientations are correlated with the thermal fluctuations of the particle positions. As discussed in Sec. 2.2.1, to extract this information, which is encoded in the distribution of the collection of functions $\{\Gamma_{\ell m}(\hat{\mathbf{k}})\}$, we examine the order-parameter component $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$:

$$\begin{aligned} q\,W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) &= q\int d\tau\, d\{\Sigma\}\,\mathcal{D}\{\Gamma\}\,P(\tau,\{\Sigma\},\{\Gamma\})\,\Gamma_{1,m_1}(\mathbf{k}^{\alpha_1})\,\mathrm{e}^{-\hat{\mathbf{k}}^2/2\tau} \\ &= \Big[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\Big\langle\Big(\mathrm{e}^{-i\mathbf{k}^{\alpha_1}\cdot(\mathbf{c}_j-\mu_j)}-\langle\mathrm{e}^{-i\mathbf{k}^{\alpha_1}\cdot(\mathbf{c}_j-\mu_j)}\rangle\Big) \\ &\qquad\times\Big(Y^*_{1m_1}(\mathbf{s}_{j,a})-\langle Y^*_{1m_1}(\mathbf{s}_{j,a})\rangle\Big)\Big\rangle\Big] \\ &= \frac{2\epsilon}{3}\frac{i\mathcal{C}^{(1)}}{\sqrt{3}}\,k^{\alpha_1\,*}_{m_1}\,\frac{\delta_{\tilde{\mathbf{k}},\mathbf{0}}}{\sqrt{4\pi}}\int_0^\infty d\theta\,\pi(\theta)\,\mathrm{e}^{-\hat{\mathbf{k}}^2/\epsilon\theta}. \end{aligned} \tag{5.4}$$

By considering the derivative with respect to $\mathbf{k}^{\alpha_1}$, taking the limit $\hat{\mathbf{k}}\to\hat{\mathbf{0}}$, and contracting, we obtain

$$\left[\frac{1}{N}\sum_{j=1}^{N}\frac{1}{A}\sum_{a=1}^{A}\Big\langle(\mathbf{c}_j-\langle\mathbf{c}_j\rangle)\cdot(\mathbf{s}_{j,a}-\langle\mathbf{s}_{j,a}\rangle)\Big\rangle\right]\approx-\frac{\epsilon}{\sqrt{3\pi}}\,\mathcal{C}^{(1)} \tag{5.5}$$

characterizing the anticorrelation (as $\mathcal{C}^{(1)}$ is positive) of the thermal orientation-fluctuations of orbitals with the thermal position-fluctuations of the particles to which the orbitals are attached.

5.4 Scaling and its Indications

In the previous two subsections we have obtained explicit physical information about the amorphous solid state in the vicinity of the solidification transition from the three lowest angular-momentum components of the order parameter. We now address in more generality the manner in which various physical quantities reflecting the orientational ordering scale with ϵ. To do this, we examine the scaling of various components of the order parameter, established in Sec. 4.5.3. Hence, we have the following scaling for various moments[1] of the joint probability distribution P associated with localized particles ($\tilde{\ell} \neq 0$):

$$\int d\tau \, d\{\Sigma\} \, \mathcal{D}\{\Gamma\} \, P(\tau, \{\Sigma\}, \{\Gamma\}) \, \hat{\Sigma}_{\hat{\ell}\hat{m}} \sim \epsilon^{1+\tilde{\ell}/2}, \tag{5.6}$$

$$\int d\tau \, d\{\Sigma\} \, \mathcal{D}\{\Gamma\} \, P(\tau, \{\Sigma\}, \{\Gamma\}) \, \hat{\Gamma}_{\hat{\ell}\hat{m}}(\hat{\mathbf{k}}) \exp\left(-\hat{\mathbf{k}}^2/2\tau\right) \sim k^{\tilde{\ell}} \sim \epsilon^{\tilde{\ell}/2}, \tag{5.7}$$

the latter being valid for $\hat{\mathbf{k}}^2 \sim \epsilon$. Note the exponent $1 + \tilde{\ell}/2$ in Eq. (5.6).

We now describe a plausible physical scenario that is consistent with this scaling of P. Near to the transition the network has many long chains consisting of twice-bonded particles, with only the occasional more highly-bonded particles linking those chains together. Thus most of the localized particles are on extremely mobile segments. Orbitals attached to particles on such segments are likely to be even less localized, orientationally, than orbitals on less mobile segments, such as those near junctions between chains. Consider, for the sake of illustration, a dangling chain (i.e., a chain of particles attached to the network only at one end). The orientational fluctuations of successive orbitals compound the fluctuations of the orbitals farther from the junction, causing them to be successively more delocalized. This compounding of fluctuations so heavily suppresses

[1] Note that we have not obtained an algorithm capable of yielding the leading-order scaling of *all* moments of the joint probability distribution P, even though we have obtained the leading-order behavior of all the components of the order parameter. Indeed, there is no reason for *every* moment of P to contribute to the leading-order behavior of the components of the order parameter.

orientational localization that it causes the scaling (and not just the numerical value) of the orientational localization characteristics $\Sigma_{\ell m}$ to vary according to location in the network. Moreover, because orientational localization is heavily suppressed for such a large fraction of orbitals, the leading-order scaling of the moments of $\Sigma_{\ell m}$ is dominated by contributions from the small fraction of better-localized orbitals (e.g., those near chain junctions), and is blind to the much larger fraction of less well-localized orbitals (e.g., those far from chain junctions). This partitioning of localized orbitals into better and less well fractions yields a picture consistent with our results, provided we assume that the better localized variety constitute a fraction of order ϵ of the localized orbitals. This fraction manifests itself in the exponent $1+\tilde{\ell}/2$ in Eq. (5.6) as the additional 1. This picture allows us to identify the following appealing scaling for the localization characteristics of the better localized orbitals:

$$\Sigma_{\ell m} \sim \epsilon^{\ell/2}, \tag{5.8}$$

$$\Gamma_{\ell m}(\hat{\mathbf{k}}) \sim k^{\ell} \sim \epsilon^{\ell/2}, \tag{5.9}$$

the latter being valid for $\hat{\mathbf{k}}^2 \sim \epsilon$. Note, in particular, that this scaling indicates that for a better localized orbital

$$\frac{\Big\langle (\mathbf{c}_j - \langle \mathbf{c}_j \rangle) \cdot (\mathbf{s}_{j,a} - \langle \mathbf{s}_{j,a} \rangle) \Big\rangle}{\sqrt{\Big\langle (\mathbf{c}_j - \langle \mathbf{c}_j \rangle)^2 \Big\rangle \Big\langle \mathbf{s}_{j,a} \Big\rangle^2}} \sim 1 \tag{5.10}$$

implying that the orientational-positional thermal fluctuation correlations are strong for all bond densities in the vicinity of the amorphous solidification transition. Whilst we cannot be certain that this scenario is a necessary consequence of our results, it is both consistent with them and physically plausible.

5.5 Remarks on the Theoretical Description

The primary result of our theoretical analysis of the model of vitreous media is a statistical characterization of the structure and heterogeneity of the equilibrium amorphous solid state that emerges due to the random permanent covalent bonding of the constituent particles. This statistical characterization takes the form of a joint probability distribution that ascertains the likelihood of finding a particle: (i) to be localized, (ii) to have a certain positional localization length, (iii) for a bond connected to this particle to have a certain orientational localization characteristics, and (iv) for the correlations between the thermal fluctuations in particle position and orbital orientation to have certain characteristics.

We expect the resulting statistical characterization to be valid beyond the context of the concrete model used to determine it. The reason for this is that, apart from certain simple dependences on physical parameters describing the particles in the network, this characterization is in fact a consequence of the order parameter that we have considered, the symmetries of the Landau-type free energy associated with this order parameter, and a limited number of further assumptions. Testing the ranges of validity of this statistical characterization will be one of the central themes of the numerical simulations to be described in the next Chapter.

CHAPTER 6

NUMERICAL SIMULATIONS

6.1 Dynamical Model

We have constructed an analytical approach to the equilibrium structure of the amorphous solid state of a class of materials, such as silica gels, formed by the permanent random covalent bonding of atoms or small molecules. Having presented this analytical treatment of a model of such materials, we shall now move on to numerical simulations of a system based on our model. These simulations are very similar in spirit to the simulations undertaken by Barsky and Plischke in the context of macromolecular media and described in Ref. [8]. In performing the numerical simulations our aims were: (i) to test the assumptions of the analytical treatment, (ii) to test the predictions of the analytical theory and (iii) to obtain insight into the structure of the system in regimes where certain assumptions invoked to allow analytical progress are invalid, so as to better understand their implications.

We begin by describing the system that is the focus of the numerical simulations. This system is closely related to the theoretical model described in Chapter 2, and is intended to have very similar properties. It consists of a large number N of particles, each possessing four orbitals (i.e., $A = 4$) by means of which it is capable of forming permanent covalent bonds with other such particles. These particles are envisioned to populate a cubic system, upon which periodic boundary conditions are imposed (in order to reduce finite-size effects). Lengths are measured in units of the bond-length σ, usually set to 1.

The particles are taken to interact with each other via a truncated repulsive potential

$$U_{ij}^{\text{rep}} = \begin{cases} C_{\text{rep}} \left(\frac{r_{ij}}{R_{\text{hs}}\,\sigma}\right)^{-6} & , \quad r_{ij} < R_{\max}\,\sigma \\ 0 & , \quad r_{ij} > R_{\max}\,\sigma \end{cases} , \tag{6.1}$$

where C_{rep} controls the strength, R_{hs} the range, and $R_{\max}$ the maximum range of the repulsive interaction between the particles. As we are primarily concerned with *universal* properties of amorphous systems, the specific choice of potential should make very little difference, as long as it satisfies the conditions outlined in Sec. 2.1 (i.e., that the potential should stabilize the system against the formation of crystalline, molecular crystalline, or phase separated states, with the added condition that chains of bonded particles should be unable to pass through each other). In reality, this merely amounts to choosing a sufficiently strong repulsive potential. Details of the interaction [including both the form of the potential (6.1) and the values of the parameters $C_r, R_{\text{hs}}, R_{\max}$] were, indeed, found to be inconsequential to the properties of the amorphous solid state, just as they do not feature in the analytical treatment of the model.

Orbitals of a single particle are also taken to repel one another. Unlike in the analytical model, for which it was sufficient for us to specify the two-orbital correlator, for a molecular dynamics simulation of the system we need to provide the form and strength of the interaction between the orbitals. This was done by specifying the torque, acting on an orbital due to its interaction with another orbital of the same particle to have magnitude

$$\tau = T_{\text{rep}} \ln\left[\left(1 - \cos\phi\right)/2\right], \tag{6.2}$$

where ϕ is the angle between the two orbitals and T_{rep} controls the strength of this inter-orbital repulsion. Again, as we are only interested in universal properties of the system, we expect the details of the inter-orbital interaction to be irrelevant. They were indeed found to make little difference, as long as they obeyed the basic assumptions of the analytical model, viz., that the interaction be repulsive and that the mechanical equilibrium configuration of a free particle be a tetrahedral arrangement of the orbitals (see Sec. 2.1). This lack of dependence on the details of the angular interaction was checked by varying the parameter T_{rep} as well as the form of the torque (6.2). The properties of the system were found to be essentially insensitive to these variations.

The particles are also subject to random thermal forces (the source of these forces can be considered to be the effect of the molecules of the solvent). We assume an overdamped regime, so that the displacement of particle j in a timestep Δt was taken to be

$$\Delta \mathbf{r}_j = \frac{\mathbf{F}_j}{\eta} \Delta t, \tag{6.3}$$

where $\mathbf{F}_j$ is the total force acting on particle j and η is the effective viscosity. Angular displacements of the orbitals was treated similarly, with the angular displacement of a free orbital (i.e., an orbital that is not part of a covalent bond) taken to be

$$\Delta \mathbf{s}_{j,a} = \frac{\tau_{j,a} \times \mathbf{s}_{j,a}}{\eta_{\text{ang}}} \Delta t, \tag{6.4}$$

where $\tau_{j,a}$ is the total torque acting on orbital $\mathbf{s}_{j,a}$ and η_{ang} is the effective angular viscosity. An orbital that is part of a covalent bond between two particles is, of course, constrained to connect the two particles and thus no equation of motion is needed for such an orbital, rather the torque acting on it is figured into the force acting on the particles.

Note that as the amorphous solidification transition occurs not due to lowering the temperature but due to the increase in the number of permanent bonds, we have no need to specify the temperature explicitly (just as temperature is absent from the analytical theory). We merely provide a random noise in the form of random forces acting on the particles, controlled by the parameter D which, through the Fluctuation-Dissipation

Theorem, is equivalent to the temperature. Thanks to the Central Limit Theorem it is not necessary to generate a Gaussian distribution for the random forces, so the random forces were taken to have constant magnitude and random directions.

6.2 Computational Procedure

The particles were first equilibrated as a melt at a density of $\rho\sigma^3 = 1.0$. As the inter-particle interaction is taken to be independent of the orientation of the orbitals, at this stage of the simulation the orientations of the orbitals were ignored. Compared to the simulations described in Ref. [8], the equilibration times of the melt were found to be quite short, around 1×10^5 timesteps, due to the fact that issues of entanglement, important in the case of macromolecular media, are absent in the present setting of small molecules.

Random permanent covalent bonds were then introduced into the system. The Deam-Edwards distribution calls for a finite probability to be associated with the formation of each bond. Loosely speaking, this probability depends on the likelihood of finding the liquid in the configuration that results after all the bonds are introduced (see Sec. 3.1.2 for more detail). The mean number of bonds is controlled by the parameter μ^2. Implementing the Deam-Edwards distribution exactly as specified in Sec. 3.1.2 for the analytical model is not feasible, as it would imply sampling large ensembles of possible bond configurations and computing the partition function for each configuration. That procedure would be extremely computationally demanding. The essential features of the Deam-Edwards distribution, however, can be captured by the following simple procedure, designed to mimic the process possible in physical experiments. We associate with each pair of particles the probability that a bond is formed between them, this probability being dependent on the distance between the two particles. Note that this method is different from the exact prescription for generating the Deam-Edwards distribution because we associate a separate probability with each individual possible bond, whereas the Deam-Edwards distribution does not factorize over the bonds. However, the implications of both approaches are very similar – that bonds between particles which are far from each other are very unlikely to form. Though different forms for the dependence of the probability of bond formation on the inter-particle separation could be used, the results were found to be independent of its details. The following simple form was used:

$$p_{ij} = \begin{cases} p & , \quad r_{ij} < R_{\text{cross}}\,\sigma \\ 0 & , \quad r_{ij} > R_{\text{cross}}\,\sigma \end{cases} , \tag{6.5}$$

which amounts to associating a certain fixed probability with the formation of a covalent bond between particles that are within a distance R_{cross} from each other. Although under the distribution described in Sec. 3.1.2 only the mean (but not the total) number of bonds is fixed, due to the fairly small size of the systems studied (1000 particles in most cases) it was found to be more effective to control the total number M of covalent bonds instead. For convenience purposes we define the crosslink density m via $m \equiv M/N$.

To implement the crosslinking procedure, first a list of possible bonds was created, as dictated by Eq. 6.5. Out of the possible bonds the required number was then selected, one at a time, ensuring that no particle was bonded to more than four other particles (i.e., that no particle was involved in more bonds than it has orbitals). The selected bonds were then implemented by imposing a spring potential between the pair of particles, given by

$$U_{ij}^{\text{bond}} = \frac{C_{\text{bond}}}{2}\left(\frac{r_{ij}-\sigma}{\sigma}\right)^2 , \tag{6.6}$$

where the parameter C_{bond} measures the strength of the bonds. Note that the equilibrium length of a bond is σ. It must be noted that in the analytical theory the bonds are taken to be completely rigid which, if incorporated into the numerical model, would introduce serious computational complications; thus rigid bonds were approximated by assigning a large value to the parameter C_{bond}. The universal properties of the system were found to be independent of C_{bond}, as long as the bond interaction kept the particles close enough to prevent chains of linked particles from passing through one another, so it is reasonable to expect that the results would not be very different if rigid bonds had been implemented.

The resulting system was then equilibrated for 3×10^6 to 6×10^6 timesteps. After equilibration, various data were collected, the primary focus being the fraction of localized particles q and the distribution of localization lengths $p(\xi)$. Even though q is defined as the fraction of particles with finite localization lengths, both the analytical theory and empirical observations show that these are simply the particles comprising the "infinite" cluster. In the thermodynamic limit, percolation theory shows [15] that there is only one cluster of size comparable to the size of the sample, however; in a system of finite size there is a possibility for more than one such cluster to exist. Empirical cluster-size analysis, however, has shown that this is not the case. Thus the "infinite" cluster was simply taken to be the largest cluster present. The parameter q was then taken to be the number of particles in that cluster divided by the total number of particles N.

As for the distribution of localization lengths $p(\xi)$, two methods for its extraction exist. One is the method followed by Barsky and Plischke [8], and consists of calculating the isotropic component of the order parameter (2.6) in the two-replica sector for a range of values of the wave-vector $\mathbf{k}$ and then extracting the distribution $p(\xi)$ from it. However, in the present setting it is simpler to make direct use of the definition of the joint probability distribution. The expression for $p(\xi)$ then becomes

$$p(\xi) = \left[\frac{1}{N} \sum_{j=1}^{N} \delta(\xi - \xi_j) \right], \tag{6.7}$$

and calculating it amounts to collecting a histogram of the r.m.s. displacements of particles from their mean positions for the particles comprising the solid state (that is, the particles that are part of the cluster that spans the system). This calculation can be further simplified by keeping the center-of-mass of the sample fixed, so that there is no collective motion of the particles. (Recall that periodic boundary conditions do not conflict with MTI.) All quantities of interest were averaged over several (usually five) runs (i.e., realizations of the disorder).

6.3 Results



Figure 6.1 Fraction of localized particles versus crosslink density. The dotted line is a "guide to deceive the eye.'

In Fig. 6.1 we present a plot of the fraction of localized particles as a function of the crosslink density. We can see that the transition occurs at a critical crosslink density m_c of around 0.75, which, while inconsistent with the predictions of mean-field theory, is similar to values obtained for bond percolation on a three-dimensional diamond lattice [15]. Note that the prediction of the mean-field theory is that $q \propto \epsilon^{\beta}$ with $\beta = 1$. While the plot in Fig. 6.1 is consistent with this prediction, it is important to note that the fit is obtained through the use of points fairly far from the transition. Data close to the transition is difficult to obtain, due to the large fluctuations in the measured quantities. Hence the evidence gathered is insufficient to rule out a different value for β.



Figure 6.2 Scaled distribution of localization lengths near the transition for two values of the crosslink density.

As stated in Sec. 5.5, among the main results of the analytical theory is a universal distribution of localization lengths. We can test this result by comparing the distribution of localization lengths obtained in the molecular dynamics simulations with the analytical predictions. Figure 6.2 displays the scaled distributions of localization lengths for several values of the crosslink density m, along with the parameter-free curve obtained from the analytical approach (see Sec. 5.2). The horizontal axis is in units of the average localization length $\bar{\xi}$ (which varies with the crosslink density) and the area under each curve is normalized to unity. Note that the data for the range of crosslink densities collapses fairly well on to a single curve, supporting the claim that the distribution is governed by a universal scaling law. Furthermore, agreement with the analytical curve is quite good, especially considering that the fit is parameter-free.



Figure 6.3 Distribution of relative localization lengths far from the transition

The analytical theory, developed in Chapters 2 to 5 is expected to be valid in the vicinity of the transition, where the expansion in powers of the departure from the critical crosslink density is justified. Far from the transition we would expect the results of molecular dynamics simulations to differ significantly from the analytical predictions. To gain a better understanding of the limitations of the analytical theory, it is interesting to see how the form of the scaled distribution of localization lengths evolves as the crosslink density moves away from its critical value. Figure 6.3 presents the distributions of localization lengths for several rather large values of the crosslink density. Note that as the density of crosslinks is increased, the distribution becomes rather more sharply peaked. This may be explained, in part, by considering the sources of microstructural randomness in the system (i.e., the heterogeneity of the environments that the particles find themselves in). As we move closer to saturating the number of bonds in the system (note that the maximum density of bonds is $m = 2$, as each bond requires two orbitals and there are four orbitals attached to every particle) although the network remains architecturally random, the fluctuations in the coordination numbers of the particles become smaller, as more and more particles become bonded to neighbors via all four of their orbitals. Although this is only one possible explanation for the sharpening of the peak of the distribution of localization lengths, it does seem to make intuitive sense.

The central result of these numerical simulations must be considered to be the robustness of the scaled distribution of localization lengths. It has been observed to be insensitive to the details of all interactions (Eqs. 6.1, 6.2, 6.6) as well as to the values of the parameters of the model (e.g., $C_{\rm rep}, C_{\rm bond}, T_{\rm rep}$, etc.). It is also fairly insensitive to the crosslink density, as long as this remains far from its saturation value of $m = 2$, and even deep in the ordered phase the scaled distribution is qualitatively rather similar to the critical value. Indeed, the distribution has been found to have this form even if the system was not allowed to equilibrate fully (this has also been suggested in ref. [8]). In preliminary investigations of ours the same distribution was even obtained in the context of a densely crosslinked liquid (i.e., for crosslink densities *below* the transition). It is also the same for macromolecular media and for the low-molecular-weight random networks under consideration here. Overall, this robustness of the distribution supports the claim that it is a universal consequence of the symmetries of the system, as was argued from a Landau-theory perspective by Peng and collaborators in Ref. [9].

CHAPTER 7

SUMMARY AND CONCLUSIONS

In this Thesis we have developed an analytical theory of vitreous media and reported the results of MD simulations aimed at testing the predictions of this theory and at exploring the domain of its applicability. We have developed a rich description of the underlying heterogeneity of the amorphous solid state in terms of a joint probability distribution, arising from an order parameter capturing several essential properties of the amorphous solid state. Our numerical simulations provide evidence for the validity of this description. Furthermore, they support the notion that this statistical description is not restricted to the context in which we have developed it, but rather is a universal property of the amorphous solid state, arising from the form of the order parameter and the symmetries of the system. We have also seen how this statistical description changes in regimes in which some of the assumptions of the analytical theory no longer strictly hold. We hope that this kind of approach to the inherent heterogeneity of amorphous systems would be useful in studying conventional glassy systems as well.

However, the accuracy and scope of these results is limited in several significant ways. These limitations of our descriptions present exciting avenues for further research. Let us briefly examine some of these limitations and the research opportunities they present.

In this work we have focused on *equilibrium* structural properties. It would be interesting to obtain analytical results concerning the dynamics of the amorphous solid state. Numerical simulations could also prove useful here. Studying the dynamics might provide further insight into the dynamics of the glassy state, where the constraints are not permanent, but rather are a consequence of short-lived correlations in the system, bringing us one step closer to an understanding of glassy systems.

We have worked *near* to the amorphous solidification transition and, although we have obtained some results for higher crosslink densities by means of numerical simulations and provided a qualitative argument for their physical meaning, it would be interesting to obtain an analytical description that could provide us with a better understanding of the nature of the highly-crosslinked regime of amorphous systems. Window glass, for example, would fall under this category, if one should accept the constraints as permanent.

We have computed within a *mean-field* framework. While in the context of crosslinked macromolecules of significant length, as argued by de Gennes [16] and established by Peng and Goldbart's Renormalization Group theory [17], mean-field theory is accurate, the context of vitreous media provides an excellent opportunity to study the limitations of mean-field theory of amorphous media, both from theoretical, computational, and experimental standpoint. Increased insight in this area would also further our understanding of the applicability and limitations of mean-field theory in the context of glassy systems.

More insight on the amorphous solid state could be obtained by obtaining physical information not contained in our order parameter, such as, e.g., correlations in localization lengths and other diagnostics of the behavior of the system. Again, there is plenty of room for both analytical and numerical progress.

Despite these limitations, we have gained knowledge about the amorphous solid state. We have also developed a body of analytical and computational methods which we can expect to be applicable beyond the context in which we have used them in this work. We have also laid the groundwork for further study, much of which would not only improve our understanding of the amorphous solid state, but also further our efforts in the study of conventional glassy systems.

APPENDIX A

CONSTANT DEFINITIONS AND MATHEMATICAL FORMULAE

A.1 Useful Mathematical Ingredients

Owing to the presence of the factor $\exp(i\mathbf{k}\cdot\mathbf{s})$ in the effective Hamiltonian, we shall need the Rayleigh expansion for plane waves (see Ref. [18]):

$$\exp\left(i\mathbf{k}\cdot\mathbf{r}\right) = 4\pi\sum_{\ell=0}^{\infty}\sum_{m=-\ell}^{\ell} i^{\ell}\, j_{\ell}(kr)\, Y^{*}_{\ell m}(\mathbf{k}/k)\, Y_{\ell m}(\mathbf{r}/r), \tag{A.1}$$

where $j_\ell(\rho)$ is a spherical Bessel function, i.e., $j_\ell(\rho) \equiv \sqrt{\pi/2\rho}\, J_{\ell+\frac{1}{2}}(z)$. The small-$z$ asymptotics of $j_\ell(z)$ are (see Ref. [19]):

$$j_\ell(z) \sim \frac{z^\ell}{1\cdot 3\cdot 5\cdot(2\ell+1)}\left(1-\frac{z^2/2}{1!(2\ell+3)}\right). \tag{A.2}$$

In particular:

$$j_0(z) \sim 1 - z^2/6, \tag{A.3}$$

$$j_1(z) \sim z/3. \tag{A.4}$$

We also need the Clebsch-Gordan decomposition for spherical harmonic functions, i.e.,

$$Y_{\ell_1 m_1}(\mathbf{s})\, Y_{\ell_2 m_2}(\mathbf{s}) = \sum_{\ell_3 m_3}\sqrt{\frac{(2\ell_1+1)(2\ell_2+1)(2\ell_3+1)}{4\pi}}\begin{pmatrix}\ell_1 & \ell_2 & \ell_3\\ m_1 & m_2 & m_3\end{pmatrix} Y^{*}_{\ell_3 m_3}(\mathbf{s})\begin{pmatrix}\ell_1 & \ell_2 & \ell_3\\ 0 & 0 & 0\end{pmatrix}, \tag{A.5}$$

as well as the complex-conjugation and parity-transformation formulæ for spherical harmonic functions,

$$
\begin{aligned}
Y^*_{\ell m}(\mathbf{s}) &= (-1)^m \, Y_{\ell\, -m}(\mathbf{s}), && \text{(A.6)} \\
Y_{\ell m}(-\mathbf{s}) &= (-1)^\ell \, Y_{\ell m}(\mathbf{s}). && \text{(A.7)}
\end{aligned}
$$

We shall also find it convenient to make use of angular-momentum-one spherical components of vectors:

$$
k^*_m \equiv \sqrt{\frac{4\pi}{3}} \, k \, Y^*_{1m}(\mathbf{k}/k) \tag{A.8}
$$

We shall be making use of Wigner 3-j symbols, and shall need some of their basic properties. From [18] specialised to the case $\ell_3 = m_3 = 0$, and using the orthonormality of the spherical harmonic functions, we have

$$
\sqrt{(2\ell_1+1)(2\ell_2+1)} \begin{pmatrix} \ell_1 & \ell_2 & 0 \\ 0 & 0 & 0 \end{pmatrix} \begin{pmatrix} \ell_1 & \ell_2 & 0 \\ m_1 & m_2 & 0 \end{pmatrix} = \delta_{\ell_1,\ell_2} \, \delta_{m_1+m_2,0} \, (-1)^{m_2}. \tag{A.9}
$$

Even permutations of the columns in Wigner 3-j symbols leave the values unchanged:

$$
\begin{pmatrix} \ell_1 & \ell_2 & \ell_3 \\ m_1 & m_2 & m_3 \end{pmatrix} = \begin{pmatrix} \ell_2 & \ell_3 & \ell_1 \\ m_2 & m_3 & m_1 \end{pmatrix} = \begin{pmatrix} \ell_3 & \ell_1 & \ell_2 \\ m_3 & m_1 & m_2 \end{pmatrix}. \tag{A.10}
$$

Odd permutations of the columns in Wigner 3-j symbols is equivalent to multiplication by $(-1)^{\ell_1+\ell_2+\ell_3}$. We also have

$$
\begin{pmatrix} \ell_1 & \ell_2 & \ell_3 \\ m_1 & m_2 & m_3 \end{pmatrix} = (-1)^{\ell_1+\ell_2+\ell_3} \begin{pmatrix} \ell_2 & \ell_3 & \ell_1 \\ -m_2 & -m_3 & -m_1 \end{pmatrix}. \tag{A.11}
$$

Consequently, if $\ell_1 + \ell_2 + \ell_3$ is odd, then

$$
\begin{pmatrix} \ell_1 & \ell_2 & \ell_3 \\ 0 & 0 & 0 \end{pmatrix} = 0. \tag{A.12}
$$

Also, we need the special case

$$
\begin{pmatrix} 1 & 1 & 0 \\ m_1 & m_2 & 0 \end{pmatrix} = \delta_{m_1+m_2,0}(-1)^{m_1} \, \frac{1}{\sqrt{3}}. \tag{A.13}
$$

A.2 Quasi-Gaussian Integrals

To perform a sum of the type $V^{-n}\sum_{\hat{\mathbf{k}}}\delta_{\tilde{\mathbf{k}},\mathbf{0}}\,\mathrm{e}^{-c\hat{\mathbf{k}}^2}$ we write

$$V^{-n}\sum_{\hat{\mathbf{k}}}\delta_{\tilde{\mathbf{k}},\mathbf{0}}\,\mathrm{e}^{-c\hat{\mathbf{k}}^2}=\left(\frac{1}{2\pi}\right)^{(n+1)d}\int\prod_{\alpha=0}^{n}\prod_{\nu=1}^{d}\left(dk_\nu^\alpha\right)\mathrm{e}^{-c\sum_{\alpha=0}^{n}\sum_{\nu=1}^{d}(k_\nu^\alpha)^2}\int\prod_{d}\left(dm_\nu\,\mathrm{e}^{im_\nu\sum_\alpha k_\nu^\alpha}\right), \tag{A.14}$$

where $\nu=1\ldots d$ runs through the ($d=3$) spatial dimensions. Performing the Gaussian k_ν^α integrals we obtain

$$\left(\frac{1}{2\pi}\right)^{(n+1)d}\int\prod_{\nu=1}^{d}\left(dm_\nu\left(\frac{4\pi}{c}\right)^{(n+1)/2}\mathrm{e}^{-m_\nu^2/4c}\right). \tag{A.15}$$

Now performing the m_ν integrals and taking the replica limit $n\to 0$ we arrive at the final result

$$V^{-n}\sum_{\hat{\mathbf{k}}}\delta_{\tilde{\mathbf{k}},\mathbf{0}}\mathrm{e}^{-c\hat{\mathbf{k}}^2}=\left(\frac{1}{2\pi}\right)^{(n+1)d}\left(\frac{4\pi}{c}\right)^{(n+1)d/2}\left(\frac{\pi c}{(n+1)}\right)^{d/2}\to 1. \tag{A.16}$$

Sums of the type $V^{-n}\sum_{\hat{\mathbf{k}}}\mathcal{F}(\hat{\mathbf{k}})\delta_{\tilde{\mathbf{k}},\mathbf{0}}\mathrm{e}^{-c\hat{\mathbf{k}}^2}$, where $\mathcal{F}(\hat{\mathbf{k}})$ is a polynomial in $(k^\alpha)_m^{(\ell)}$ (i.e., the spherical components of the $\mathbf{k}^\alpha$) are performed similarly.

A.3 Definitions of the $\mathcal{C}^{(n)}$ Constants

The $\mathcal{C}^{(n)}$ constants are defined as follows:

$$\mathcal{C}^{(0)} \equiv A^{-1}\left(1+(A-1)C_1\right) \tag{A.17}$$

$$\mathcal{C}^{(1)} \equiv \frac{1}{1+\mathcal{C}^{(0)}} \tag{A.18}$$

$$\mathcal{C}^{(2)} \equiv \frac{1}{A}\left(1+(A-1){C_1}^2\right) \tag{A.19}$$

$$\mathcal{C}^{(3)} \equiv \mathcal{C}^{(2)}-2\mathcal{C}^{(2)}\mathcal{C}^{(1)} \tag{A.20}$$

$$\mathcal{C}^{(4)} \equiv \frac{1-\mathcal{C}^{(2)}}{\mathcal{C}^{(2)}} \tag{A.21}$$

$$\mathcal{C}^{(5)} \equiv \frac{\mathcal{C}^{(3)}}{3\mathcal{C}^{(2)}\mathcal{C}^{(4)}} \tag{A.22}$$

$$\mathcal{C}^{(6)} \equiv \frac{\mathcal{C}^{(3)}}{12\mathcal{C}^{(2)}{\mathcal{C}^{(4)}}^2}+\frac{{\mathcal{C}^{(1)}}^2}{8\mathcal{C}^{(4)}} \tag{A.23}$$

They encode information about the strength of the mutual repulsion of orbitals. All of them are positive.

APPENDIX B

TECHNICAL DETAILS OF CALCULATIONS

B.1 Averaging over the Deam-Edwards Distribution

In this Appendix, following the discussion in Ref. [10], we perform the disorder-averaging of the n-fold replicated partition function $\tilde{Z}^n$ with respect to the Deam-Edwards distribution $\mathcal{P}_M(\mathcal{C})$, characterizing the distribution of the quenched random constraints $\mathcal{C} \equiv \{j_e, j_e'; a_e, a_e'\}_{e=1}^{M}$ (i.e., bonds), defined in Sec. 3.1.2. We start from the definition of the disorder average as a weighted average over all possible realizations of the disorder:

$$[\tilde{Z}^n(\mathcal{C})] \equiv \mathrm{Tr}_{\mathcal{C}}\, \mathcal{P}_M(\mathcal{C})\, \tilde{Z}^n(\mathcal{C}), \tag{B.1}$$

where $\mathrm{Tr}_{\mathcal{C}}$ denotes a trace over all possible realizations of the disorder $\mathcal{C}$, defined via:

$$\mathrm{Tr}_{\mathcal{C}} \cdots \equiv \frac{1}{\mathcal{N}} \sum_{M=0}^{\infty} \prod_{e=1}^{M} \left(\sum_{j_e, a_e} \sum_{j_e', a_e'} \right) \cdots. \tag{B.2}$$

Here, $\mathcal{N}$ is a normalization factor which we shall compute below, and the sum over M represents summing over all possible numbers of permanent covalent bonds. Note that our definition of the Deam-Edwards distribution $\mathcal{P}_M(\mathcal{C})$ includes the weighting factor $1/M!(2\pi\mu^2 V/N)^M$ which is a quasi-Poissonian probability distribution for the number of bonds M, controlled by the parameter μ^2. Hence

$$
\begin{aligned}
[\tilde{Z}^n(\mathcal{C})] \quad &\equiv \quad \frac{1}{\mathcal{N}}\sum_{M=0}^{\infty}\frac{(2\pi V\mu^2/NA^2)^M}{M!}\prod_{e=1}^{M}\Bigg(\sum_{j_e,a_e}\sum_{j'_e,a'_e}\Bigg) \\
&\qquad \Big\langle \prod_{e=1}^{M}\delta^{(3)}(\mathbf{c}_{j_e}+\frac{1}{2}\mathbf{s}_{j_e,a_e}-\mathbf{c}_{j'_e}-\frac{1}{2}\mathbf{s}_{j'_e,a'_e})\,\Delta^{(2)}(\mathbf{s}_{j_e,a_e}+\mathbf{s}_{j'_e,a'_e})\Big\rangle_{N,1}^{(n+1)}, \quad \text{(B.3)}
\end{aligned}
$$

It is worth noting that the sums over j_e, j'_e, a_e, and a'_e are not restricted to preclude the situation where a particular orbital a on a particular particle j is bonded to two (or more) other orbitals attached to other particles, an unphysical situation, as covalent bonds are typically regarded as "saturable," i.e., any orbital can be bonded to at most one other orbital. However, near the amorphous solidification transition the bond density is low, and thus we expect the occurrence of such multiply-bonded orbitals to be negligibly rare and not having much impact on the theory.

Introducing replicas, denoting by $\langle \cdots \rangle_{N,n+1}$ the thermal average weighted by a Hamiltonian that does not couple the replicas, and resumming the power series in M, we can rewrite Eq. (B.3) in the final form

$$
[\tilde{Z}^n(\mathcal{C})] \quad \equiv \quad \mathcal{Z}_{n+1}/\mathcal{Z}_1, \qquad \text{(B.4)}
$$

$$
\begin{aligned}
\mathcal{Z}_{n+1} \quad &= \\
&\Bigg\langle \exp\Bigg(\frac{2\pi V\mu^2}{NA^2}\sum_{j,j'=1}^{N}\sum_{a,a'=1}^{A}\prod_{\alpha=0}^{n}\delta^{(3)}(\mathbf{c}_j^\alpha+\tfrac{1}{2}\mathbf{s}_{j,a}^\alpha-\mathbf{c}_{j'}^\alpha-\tfrac{1}{2}\mathbf{s}_{j',a'}^\alpha)\,\Delta^{(2)}(\mathbf{s}_{j,a}^\alpha,-\mathbf{s}_{j',a'}^\alpha)\Bigg)\Bigg\rangle_{N,n+1} \\
&\qquad \text{(B.5)}
\end{aligned}
$$

B.2 Denominator for the Self-Consistent Equation

In this Appendix we evaluate the denominator of the right-hand side of the SCE for $\Omega(\hat{\mathbf{k}};\hat{\ell},\hat{m})$, Eq. (4.2), viz., the quantity

$$
\Bigg\langle \exp\Bigg(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}}\hat{\ell}\hat{m}}W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_a)\Bigg)\Bigg\rangle_{1,n+1}. \qquad \text{(B.6)}
$$

To do this, we expand the exponential in a power series and consider the r-th order term:

$$
\Bigg\langle \frac{1}{r!}\left(4\pi\mu^2\right)^r q^r V^{-nr}\sum_{\hat{\mathbf{k}}_1\hat{\ell}_1\hat{m}_1}\sum_{\hat{\mathbf{k}}_2\hat{\ell}_2\hat{m}_2}\cdots\sum_{\hat{\mathbf{k}}_r\hat{\ell}_r\hat{m}_r}
$$

$$W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1)\,W(\hat{\mathbf{k}}_2;\hat{\ell}_2,\hat{m}_2)\,\ldots W(\hat{\mathbf{k}}_r;\hat{\ell}_r,\hat{m}_r)\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}}\,\ldots\mathrm{e}^{i\hat{\mathbf{k}}_r\cdot\hat{\mathbf{c}}}$$
$$\times\frac{1}{A^r}\sum_{a_1,\ldots,a_r}\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2}}\ldots\mathrm{e}^{i\hat{\mathbf{k}}_r\cdot\hat{\mathbf{s}}_{a_r}}\,\hat{Y}_{\hat{\ell}_1\hat{m}_1}(-\hat{\mathbf{s}}_{a_1})\ldots\hat{Y}_{\hat{\ell}_r\hat{m}_r}(-\hat{\mathbf{s}}_{a_r})\Big\rangle_{1,n+1} \quad \text{(B.7)}$$

Noticing that the quantity (B.7) factorizes over the replicas, and passing to the replica limit $n\to 0$, we rewrite Eq. (B.7) as

$$\Big\langle\frac{1}{r!}\left(4\pi\mu^2\right)^r q^r\sum_{\mathbf{k}_1\ell_1m_1}\sum_{\mathbf{k}_2\ell_2m_2}\cdots\sum_{\mathbf{k}_r\ell_rm_r}$$
$$W(\mathbf{k}_1;\ell_1,m_1)\,W(\mathbf{k}_2;\ell_2,m_2)\,\ldots W(\mathbf{k}_r;\ell_r,m_r)\,\mathrm{e}^{i\mathbf{k}_1\cdot\mathbf{c}}\,\mathrm{e}^{i\mathbf{k}_2\cdot\mathbf{c}}\,\ldots\mathrm{e}^{i\mathbf{k}_r\cdot\mathbf{c}}$$
$$\times\frac{1}{A^r}\sum_{a_1,\ldots,a_r}\mathrm{e}^{i\mathbf{k}_1\cdot\mathbf{s}_{a_1}}\mathrm{e}^{i\mathbf{k}_2\cdot\mathbf{s}_{a_2}}\ldots\mathrm{e}^{i\mathbf{k}_r\cdot\mathbf{s}_{a_r}}\,Y_{\ell_1m_1}(-\mathbf{s}_{a_1})\ldots Y_{\ell_rm_r}(-\mathbf{s}_{a_r})\Big\rangle_{1,1}. \quad \text{(B.8)}$$

By the MTI of $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ we know that $\tilde{\mathbf{k}}_i=\mathbf{0}$, which means that $\mathbf{k}_i=\mathbf{0}$. Also, using MRI of $W(\hat{\mathbf{k}};\hat{\ell},\hat{m})$ we see that if $\hat{\mathbf{k}}=\hat{\mathbf{0}}$ then (B.8) can only be nonzero if $\hat{\ell}=\hat{0}$ also. Knowing that $W(\hat{\mathbf{0}};\hat{0},\hat{0})=1/\sqrt{4\pi}$, we get, for the r-th order contribution $(\mu^2)^r q^r/r!$. Resumming the power series we obtain, finally

$$\Big\langle\exp\Big(\frac{4\pi\mu^2}{V^n}\sum_{\hat{\mathbf{k}}\hat{\ell}\hat{m}}W(\hat{\mathbf{k}};\hat{\ell},\hat{m})\,\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\,\frac{1}{A}\sum_{a=1}^{A}\mathrm{e}^{i\hat{\mathbf{k}}\cdot\hat{\mathbf{s}}_a}\,\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_a)\Big)\Big\rangle_{1,n+1}=\sum_{r=0}^{\infty}\frac{(\mu^2)^r q^r}{r!}=\exp(\mu^2 q). \quad \text{(B.9)}$$

B.3 Anisotropic Self–Consistent Equation: Angular Momentum One in One Replica Channel

In this Appendix we study in detail the SCE for the $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$ component. We start with the full form:

$$qW^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})=\quad(1-q)\frac{4\pi\mu^2}{V^n}\,q\sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1}W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1)$$
$$\times\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big\langle\mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\prod_{\alpha\neq\alpha_1}\left(Y_{00}(\mathbf{s}^{\alpha}_{a_0})\right)\,Y^*_{1m_1}(\mathbf{s}^{\alpha_1}_{a_0})\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\,\hat{Y}_{\hat{\ell}\hat{m}}(-\hat{\mathbf{s}}_{a_1})\Big\rangle_{1,n+1}$$
$$+\;\frac{1}{2}\left(\frac{4\pi\mu^2}{V^n}\right)^2 q^2\sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1}\sum_{\hat{\mathbf{k}}_2,\hat{\ell}_2,\hat{m}_2}W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1)\,W(\hat{\mathbf{k}}_2;\hat{\ell}_2,\hat{m}_2)$$

$$\times \frac{1}{A^3} \sum_{a_0,a_1,a_2=1}^{A} \Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}} \prod_{\alpha\neq\alpha_1}^{n} \Big(Y_{00}(\mathbf{s}_{a_0}^{\alpha_0})\Big)\; Y_{1m_1}^{*}(\mathbf{s}_{a_0}^{\alpha_1})\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}$$
$$\times \hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_{a_1})\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2}}\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_{a_2})\Big\rangle_{1,n+1} \tag{B.10}$$

We now proceed to study this equation order-by-order, starting with the linear term. As we are not interested in feedback on this component from higher angular-momentum components we may truncate the angular momentum sums to include only terms with $\hat{\ell}^2 \leq 2$. Thus we must include couplings to the components $W_{1m_2}^{\alpha_2}(\hat{\mathbf{k}})$ and $W(\hat{\mathbf{k}})$ only. We study the coupling to $W(\hat{\mathbf{k}})$ first (i.e., $\hat{\ell}_1 = \hat{m}_1 = 0$). Clearly then, in replica α_1 we must Rayleigh-expand the shift-factor $\exp(i\mathbf{k}_1^{\alpha}\cdot\mathbf{s}_{a_1}^{\alpha})$ to angular momentum 1 and put this factor equal to unity in all other replicas, obtaining

$$(1-q)\frac{4\pi\mu^2}{V^n}\, q\sum_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}_1)\,\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\left(\frac{1}{\sqrt{4\pi}}\right)^{n} Y_{1m_1}^{*}(\mathbf{s}_{a_0}^{\alpha_1})\left(\frac{1}{\sqrt{4\pi}}\right)^{(n+1)}$$
$$\times\, 4\pi i\; j_1(k_1^{\alpha_1})\sum_{m'=-1}^{1} Y_{1m'}(\mathbf{s}_{a_1}^{\alpha_1})\,Y_{1m'}^{*}\left(\frac{{\mathbf{k}_1}^{\alpha_1}}{k_1^{\alpha_1}}\right)\Big\rangle_{1,n+1}$$
$$= (1-q)\mu^2 i\,\frac{\sqrt{4\pi}}{3}W(\hat{\mathbf{k}})\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big(\delta_{a,a_1} + (1-\delta_{a,a_1})\,C_1\Big)k^{\alpha_1}\,Y_{1m_1}^{*}\left(\frac{\mathbf{k}^{\alpha_1}}{k^{\alpha_1}}\right)$$
$$= \frac{i}{\sqrt{3}}\,\mathcal{C}^{(0)}W(\hat{\mathbf{k}})\,k_{m_1}^{\alpha_1\,*}. \tag{B.11}$$

We now study the linear term corresponding to the coupling of $W_{1m_1}^{\alpha_1}(\hat{\mathbf{k}})$ to $W_{1m_2}^{\alpha_2}(\hat{\mathbf{k}})$. When $\alpha_1 \neq \alpha_2$ this term, being of order $\hat{\mathbf{k}}^2$, is subdominant. Thus we need only consider the term in the angular momentum sum where $\ell^{\alpha_1} = 1$, $\hat{\ell}_1$ being 0 in all other replicas. We examine this term in the sum, making use of the value of the two-orbital correlator, given by Eq. (4.19):

$$(1-q)\frac{4\pi\mu^2}{V^n}\, q\sum_{\hat{\mathbf{k}}_1} W_{1m_1}^{\alpha_1}(\hat{\mathbf{k}}_1)$$
$$\times\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\;\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\left(\frac{1}{\sqrt{4\pi}}\right)^{n} Y_{1m_1}^{*}(\mathbf{s}_{a_0}^{\alpha_1})\left(\frac{1}{\sqrt{4\pi}}\right)^{n} Y_{1m_1}(-\mathbf{s}_{a_1}^{\alpha_1})\Big\rangle_{1,n+1}$$

$$
\begin{aligned}
&= -(1-q)\mu^2 W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big(\delta_{a,a_1} + (1-\delta_{a,a_1})\, C_1\Big) \\
&= -(1-q)\,\mathcal{C}^{(0)}\,\mu^2 W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}). \qquad \text{(B.12)}
\end{aligned}
$$

We next proceed to examine the second-order term in Eq. (B.10). Again, we truncate the angular momentum sums. As we are only interested in the leading-order contributions to $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$ there are only two cases to consider: $\hat{\ell}_1 = \hat{\ell}_2 = \hat{0}$ and $\hat{\ell}_1^2 = 2$, $\hat{\ell}_2^2 = 0$. The former case, however, results in a term that is subdominant to term (B.11). We thus consider the latter case:

$$
\begin{aligned}
&\frac{1}{2}(1-q)\left(\frac{4\pi\mu^2}{V^n}\right)^2 q^2 \sum_{\hat{\mathbf{k}}_1,\hat{\mathbf{k}}_2} W(\hat{\mathbf{k}}_1)\, W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_2) \\
&\quad \frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\left\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}}\left(\frac{1}{\sqrt{4\pi}}\right)^{(n+1)}\left(\frac{1}{\sqrt{4\pi}}\right)^{2n} Y^{*}_{1m_1}(\mathbf{s}^{\alpha_1}_{a_0})Y_{1m_1}(-\mathbf{s}^{\alpha_1}_{a_1})\right\rangle_{1,n+1} \\
&= -\frac{\sqrt{4\pi}}{2}(1-q)\frac{\mu^4}{V^n}\sum_{\hat{\mathbf{k}}_1} q^2 W(\hat{\mathbf{k}}_1)\, W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\Big(\delta_{a,a_1} + (1-\delta_{a,a_1})\, C_1\Big) \\
&= -\frac{\sqrt{4\pi}}{2}(1-q)\mathcal{C}^{(0)}\,\frac{\mu^4}{V^n}\sum_{\hat{\mathbf{k}}_1} q^2 W(\hat{\mathbf{k}}_1)\, W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1). \qquad \text{(B.13)}
\end{aligned}
$$

Keeping in mind that due to the symmetry $\hat{\ell}_1 \leftrightarrow \hat{\ell}_2$ we must double the term (B.13), we now assemble all the terms, dropping sub-leading contributions:

$$
qW^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) = \mathcal{C}^{(0)}\Big(- qW^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) + \frac{i}{\sqrt{3}}qW(\hat{\mathbf{k}}_1)\, k^{\alpha_1\,*}_{m_1} - q^2\frac{\sqrt{4\pi}}{V^n}\textstyle\sum_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\, W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_1)\Big). \qquad \text{(B.14)}
$$

Cancelling a factor of q leaves us with Eq. (4.17).

B.4 Anisotropic Self–Consistent Equation: Angular Momentum One in Two Replica Channels

In this Appendix we study in detail the SCE for the $W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$ component. We start with the full form:

$$
\begin{aligned}
&qW^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}}) = \\
&(1-q)\frac{4\pi\mu^2}{V^n}\, q \sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1} W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1) \\
&\quad\times\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\left\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\prod_{\alpha\neq\alpha_1,\alpha_2}\left(Y_{00}(\mathbf{s}^{\alpha}_{a_0})\right)\,Y^*_{1m_1}(\mathbf{s}^{\alpha_1}_{a_0})Y^*_{1m_2}(\mathbf{s}^{\alpha_2}_{a_0})\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_{a_1})\right\rangle_{1,n+1} \\
&+\frac{1}{2}\left(\frac{4\pi\mu^2}{V^n}\right)^2 q^2\sum_{\hat{\mathbf{k}}_1,\hat{\ell}_1,\hat{m}_1}\ \sum_{\hat{\mathbf{k}}_2,\hat{\ell}_2,\hat{m}_2} W(\hat{\mathbf{k}}_1;\hat{\ell}_1,\hat{m}_1)\,W(\hat{\mathbf{k}}_2;\hat{\ell}_2,\hat{m}_2) \\
&\quad\times\frac{1}{A^3}\sum_{a_0,a_1,a_2=1}^{A}\left\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\prod_{\alpha\neq\alpha_1,\alpha_2} Y_{00}(\mathbf{s}^{\alpha_0}_{a_0})Y^*_{1m_1}(\mathbf{s}^{\alpha_1}_{a_0})Y^*_{1m_2}(\mathbf{s}^{\alpha_2}_{a_0})\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{s}}_{a_1}}\right. \\
&\qquad\left.\times\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_{a_1})\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{c}}}\,\mathrm{e}^{i\hat{\mathbf{k}}_2\cdot\hat{\mathbf{s}}_{a_2}}\hat{Y}_{\hat{\ell}\hat{m}}(\hat{\mathbf{s}}_{a_2})\right\rangle_{1,n+1}. \qquad (B.15)
\end{aligned}
$$

As we did before in App. B.3 for the SCE for $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$, we proceed to study the linear terms of this equation. Again we truncate to include only the components of W of angular momentum smaller than the angular momentum of $W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}})$, i.e. $\ell^{\alpha}=0$ for $\alpha\neq\alpha_1,\alpha_2$ and $\ell^{\alpha_1},\ell^{\alpha_2}\leq 1$. Thus we find couplings to terms $W(\hat{\mathbf{k}})$, $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$, $W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}})$, and $W^{\alpha_1\ \alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}})$. Rayleigh-expanding the shift-factor $\exp(i\mathbf{k}^{\alpha}_1\cdot\mathbf{s}^{\alpha}_{a_1})$ to angular momentum 0 or 1, as appropriate in each replica, proceeding as in Eqs. (B.12) and (B.11), and finally inserting the value for $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}})$ that we obtained in Sec. 4.5.1, we obtain the linear contribution (terms are in the order listed above):

$$
\begin{aligned}
&(1-q)\frac{4\pi\mu^2}{V^n}\, q\sum_{\hat{\mathbf{k}}_1}\frac{1}{A^2}\sum_{a_0,a_1=1}^{A}\left\langle \mathrm{e}^{-i\hat{\mathbf{k}}\cdot\hat{\mathbf{c}}}\mathrm{e}^{i\hat{\mathbf{k}}_1\cdot\hat{\mathbf{c}}}\left(\frac{1}{\sqrt{4\pi}}\right)^{n-1} Y^*_{1m_1}(\mathbf{s}^{\alpha_1}_{a_0})Y^*_{1m_2}(\mathbf{s}^{\alpha_2}_{a_0})\times\right. \\
&\quad\left\{W(\hat{\mathbf{k}}_1)\left(\frac{1}{\sqrt{4\pi}}\right)^{n+1}(4\pi i)^2\, j_1(k^{\alpha_1}_1)\, j_1(k^{\alpha_2}_1)\right. \\
&\qquad\times\sum_{m'_1,m'_2=-1}^{1} Y_{1m'_1}(\mathbf{s}^{\alpha_1}_{a_1})\,Y^*_{1m'_1}\left(\frac{{\mathbf{k}_1}^{\alpha_1}}{k^{\alpha_1}_1}\right)\,Y_{1m'_2}(\mathbf{s}^{\alpha_2}_{a_1})\,Y^*_{1m'_2}\left(\frac{{\mathbf{k}_2}^{\alpha_2}}{k^{\alpha_2}_1}\right) \\
&\qquad+W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_1)\left(\frac{1}{\sqrt{4\pi}}\right)^{n} Y_{1m_1}(-\mathbf{s}^{\alpha_1}_{a_1})4\pi i\ j_1(k^{\alpha_2}_1)\sum_{m'=-1}^{1} Y_{1m'}(\mathbf{s}^{\alpha_2}_{a_1})\,Y^*_{1m'}\left(\frac{{\mathbf{k}_1}^{\alpha_2}}{k^{\alpha_2}_1}\right) \\
&\qquad+W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}_1)\left(\frac{1}{\sqrt{4\pi}}\right)^{n} Y_{1m_2}(-\mathbf{s}^{\alpha_2}_{a_1})4\pi i\ j_1(k^{\alpha_1}_1)\sum_{m'=-1}^{1} Y_{1m'}(\mathbf{s}^{\alpha_1}_{a_1})\,Y^*_{1m'}\left(\frac{{\mathbf{k}_1}^{\alpha_1}}{k^{\alpha_1}_1}\right)
\end{aligned}
$$

$$+W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}_1)\left(\frac{1}{\sqrt{4\pi}}\right)^{n-1} Y_{1m_1}(-\mathbf{s}^{\alpha_1}_{a_1})Y_{1m_2}(-\mathbf{s}^{\alpha_2}_{a_1})\Big\}\Big\rangle_{1,n+1}$$

$$= q\,\mathcal{C}^{(2)}\left(-\frac{1}{3}k^{\alpha_1\,*}_{m_1}\,k^{\alpha_2\,*}_{m_2}\,W(\hat{\mathbf{k}}) - \frac{i}{\sqrt{3}}k^{\alpha_2\,*}_{m_2}W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}) - \frac{i}{\sqrt{3}}k^{\alpha_1\,*}_{m_1}W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}) + W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})\right)$$

$$= \mathcal{C}^{(2)}q\,W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}) - \frac{q}{3}\mathcal{C}^{(3)}k^{\alpha_1\,*}_{m_1}\,k^{\alpha_2\,*}_{m_2}\,W(\hat{\mathbf{k}}). \tag{B.16}$$

We next proceed to study the quadratic contribution to $W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$ from Eq. (B.15). Truncating the angular momentum sums, as usual, we see that there are the following four cases to consider:

(i) $\hat{\ell}_1 = \hat{\ell}_2 = 0$, corresponding to the coupling to $W(\hat{\mathbf{k}}_1)W(\hat{\mathbf{k}}_2)$,

(ii) $\hat{\ell}_1 = 0, \hat{\ell}_2^2 = 2$, corresponding to the coupling to $W(\hat{\mathbf{k}}_1)W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_2)$,

(iii) $\hat{\ell}_1^2 = \hat{\ell}_2^2 = 2$, corresponding to the coupling to $W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_1)W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}_2)$,

(iv) $\hat{\ell}_1 = 0, \hat{\ell}_2^2 = 4$, corresponding to the coupling to $W(\hat{\mathbf{k}}_1)W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}_2)$.

We study these terms in more detail, as in Appendix B.3, Eq. (B.13). Term (i) is clearly subdominant compared with the second term in Eq. (B.16). Writing out the remaining terms:

$$\text{term(ii)} : -\frac{i}{\sqrt{3}}\frac{\sqrt{4\pi}}{2}(1-q)\mathcal{C}^{(2)}\,\frac{\mu^4}{V^n}\sum_{\hat{\mathbf{k}}_1} q^2 k^{\alpha_2\,*}_{m_2}W(\hat{\mathbf{k}}_1)\,W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1), \tag{B.17}$$

$$\text{term(iii)} : \frac{\sqrt{4\pi}}{2}(1-q)\mathcal{C}^{(2)}\,\frac{\mu^4}{V^n}\sum_{\hat{\mathbf{k}}_1} q^2 W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}_1)\,W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1), \tag{B.18}$$

$$\text{term(iv)} : \frac{\sqrt{4\pi}}{2}(1-q)\mu^4\mathcal{C}^{(2)}\,\frac{\mu^4}{V^n}\sum_{\hat{\mathbf{k}}_1} q^2 W(\hat{\mathbf{k}}_1)\,W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1). \tag{B.19}$$

Term (ii) does not contribute to the leading-order behavior of $W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$ because for $\hat{\mathbf{k}}^2$ of order ϵ or greater all quadratic terms are subleading compared to linear terms, and for $\hat{\mathbf{k}}^2 \ll \epsilon$ it will be subdominant compared to terms (iii) and (iv), because of the $k^{\alpha_2\,*}_{m_2}$ factor.

Keeping in mind that, because of the symmetry $\hat{\ell}_1 \leftrightarrow \hat{\ell}_2$, we must double term (iv), we reassemble the pieces of the SCE for $W^{\alpha_1\ \alpha_2}_{1m_1 1m_2}(\hat{\mathbf{k}})$, dropping subleading contributions:

$$\begin{aligned} qW^{\alpha_1\;\alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}}) \quad = \quad & \mathcal{C}^{(2)} qW^{\alpha_1\;\alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}}) - \frac{1}{3}\mathcal{C}^{(3)} k^{\alpha_1\,*}_{m_1}\, k^{\alpha_2\,*}_{m_2}\, qW(\hat{\mathbf{k}}) \\ & + q^2\mathcal{C}^{(2)}\frac{\sqrt{4\pi}}{V^n}\sum_{\hat{\mathbf{k}}_1} W(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\, W^{\alpha_1\;\alpha_2}_{1m_1\,1m_2}(\hat{\mathbf{k}}_1) \\ & + q^2\mathcal{C}^{(2)}\frac{\sqrt{4\pi}}{2V^n}\sum_{\hat{\mathbf{k}}_1} W^{\alpha_1}_{1m_1}(\hat{\mathbf{k}}-\hat{\mathbf{k}}_1)\, W^{\alpha_2}_{1m_2}(\hat{\mathbf{k}}_1). \end{aligned} \tag{B.20}$$

Cancelling a factor of q leaves us with Eq. (4.22).

REFERENCES

[1] R. Zallen, *The Physics of Amorphous Solids.* New York: John Wiley, 1983.

[2] P. M. Goldbart *J. Phys. B*, vol. 12, p. 6585, 2000.

[3] M. Mézard, G. Parisi, and M. A. Virasoro, *Spin Glass Theory and Beyond.* Singapore: World Scientific, 1987.

[4] P. M. Goldbart and A. Zippelius *Europhys. Lett.*, vol. 27, p. 599, 1994.

[5] B. Gauthier-Manuel, E. Guyon, S. Roux, S. Gits, and F. Lefaucheux *J. Phys.*, vol. 48, p. 869, 1987.

[6] H. E. Castillo, P. M. Goldbart, and A. Zippelius *Europhys. Lett.*, vol. 28, p. 519, 1994.

[7] P. M. Goldbart, H. E. Castillo, and A. Zippelius *Adv. Phys.*, vol. 45, pp. 393–468, 1996.

[8] S. J. Barsky and M. Plischke *Phys. Rev. E*, vol. 53, p. 871, 1996.

[9] W. Peng, H. E. Castillo, P. M. Goldbart, and A. Zippelius *Phys. Rev. B*, vol. 57, p. 839, 1998.

[10] O. Theissen, A. Zippelius, and P. M. Goldbart *Int. J. Mod. Phys. B*, vol. 11, p. 1945, 1996.

[11] P. M. Goldbart and N. D. Goldenfeld *Phys. Rev. Lett.*, vol. 58, p. 2676, 1987.

[12] P. M. Goldbart and N. D. Goldenfeld *Phys. Rev. A*, vol. 39, p. 1402, 1989.

[13] P. M. Goldbart and N. D. Goldenfeld *Phys. Rev. A*, vol. 39, p. 1412, 1989.

[14] R. T. Deam and S. F. Edwards *Philos. Trans. R. Soc.*, vol. 280A, p. 317, 1976.

[15] D. Stauffer and A. Aharony, *Introduction to Percolation Theory.* New York: Taylor & Francis, 1994.

[16] P. de Gennes *J. Phys. Lett. (Paris)*, vol. 38, pp. L–1, 1976.

[17] W. Peng and P. M. Goldbart *Phys. Rev. E*, vol. 61, p. 3339, 2000.

[18] A. R. Edmonds, *Angular Momentum in Quantum Mechanics.* Princeton, New Jersey: Princeton University Press, 1974.

[19] Abramovitz and Stegun, Eds., *Handbook of Mathematical Functions.* New York: Dover Pubns., 1974.

[20] A. P. Young, Ed., *Spin Glasses and Random Fields.* Singapore: World Scientific, 1997.

[21] S. J. Barsky Ph.D. dissertation, Simon Fraser University, 1996.

VITA

KONSTANTIN A. SHAKHNOVICH

Department of Physics
University of Illinois, Urbana-Champaign
1110 West Green Street 290S
Urbana, IL, 61801, USA

Education

1996-	University of Illinois, Urbana-Champaign
1992-1996	University of Chicago, Chicago, IL
	B.S., Mathematics
	Honors B.A., Physics

Teaching Experience

1996-2000	Graduate Teaching Assistant for Undergraduate Physics Laboratory
1996-1998	Private tutor, undergraduate Physics classes

Awards and Honors

1992-1996	Dean's List
1994	Nominated for Barry Goldwater scholarship in the Physical Sciences
1996-1997	Excellence in Teaching Award
1997-1998	NSF Graduate Research Training Fellow

Publications and Conference Abstracts

K. A. Shakhnovich and P. M. Goldbart, *Statistical mechanics of random atomic and molecular networks: Structure and heterogeneity of the amorphous solid state*, Phys. Rev. B, **60**, Aug. 1999, 3862-3884.

K. A. Shakhnovich, *Statistical mechanics of random networks: Microstructure of the glass state*, APS Conference, March 1999.

A. Chubukov, D. Morr and K. Shakhovich, *Fermi surface evolution in underdoped cuprates*, Philos. Mag. B, **74**, Nov.1996, 563-71.